

## SAND

Nm. 3/90

100% (CO) COTONE

## IMPIEGO

Rett. Fin. 14 - 18 F.F. Cotton 27 - 30 GG a 1 capo

## FINISSAGGIO

Con un semplice stiro con abbondante vaporizzo si ottiene un ottimo aspetto della maglia.

Per raggiungere buona stabilità dimensionale e mano più morbida consigliamo una leggera follatura dei teli o dei capi in acqua tiepida con 2 gr./lt. di ammorbidente, quindi di centrifugare ed asciugare in tumbler senza eccedere nell'essiccazione. Finire stirando con abbondante vapore.

Sono necessarie prove preventive di finissaggio e tessitura per verificare che i capi soddisfino i requisiti richiesti.

## SAND

Nm. 3/90

100% (CO) COTTON

## KNITTING

Rett. Fin. 14 - 18 F.F. Cotton 27 - 30 GG a 1 capo

## FINISHING

Pressing with a lot of steam will give an excellent and even appearance.

To achieve maximum dimensional stability and good softness we suggest to lightly mill in water with 2 grams of softener per litre, spin dry and tumble dry without overdrying.

Steam press well.

Preliminary testing on knitting and finishing is necessary to verify that garments meet requirements.



## INDEX

027144 1B	027922 5D	290780 6A
027341 2C	● 099070 6E	● 701154 1A
027565 3C	106244 5A	701155 4A
027897 6B	205832 1C	701156 1D
027902 4E	205839 6C	● 701157 4D
027910 5E	● 205892 1E	● 701160 6D
027911 3D	205914 2D	701161 2E
027912 5C	205915 2B	701165 4B
027918 4C	252801 3E	701167 5B
027919 3B	290762 3A	701168 2A

“●” : colori disponibili in Rett. Fin. 14 / available colours in Rett. Fin 14

SAND Nm. 3/90 - 100% (CO)

	1	2	3
A	701154 ●	701168	290762
B	027144	205915	027919
C	205832	027341	027565
D	701156	205914	027911
E	205892 ●	701161	252801

4



701155

5



106244

6



290780

A



701165



701167



027897

B



027918



027912



205839

C



701157 ●



027922



701160 ●

D



027902



027910



099070 ●

E