

CASHWOOL® SWE

Nm. 2/30 - Nm. 2/48

100% (WV) LANA EXTRAFINE



IMPIEGO

Nm. 2/30

Cotton 21-24 gg	Rett. Fin. 12-14	a 1 capo
Cotton 12 gg	Rett. Fin 7-8	a 2 capi

Nm. 2/48

Cotton 27-30 gg	Rett. Fin. 14-16	a 1 capo
Cotton 21 gg	Rett. Fin 12	a 2 capi

Quantità ottimali: scatole da kg. 24.

Per colli di peso inferiore vengono applicati supplementi per minimi.

Solidità colori: secondo le norme woolmark. Eventuali esigenze particolari dovranno essere specificate all'atto dell'ordine.

FINISSAGGIO

N.B. è molto importante che la maglia sia ben battuta, in quanto utilizzando filato trattato il rientro di finissaggio è limitato e una maglia troppo lenta potrebbe ulteriormente allentarsi risultando vuota.

Pertanto consigliamo prove preventive di tessitura e finissaggio.

Lo stiro con abbondante vapore è sufficiente per ottenere un ottimo aspetto della maglia. Per esaltare la sofficità e la gonfiezza del filo, si consiglia una leggera follatura in acqua a 35°C per 3 minuti con il 2-3% di ammorbidente sul peso della merce. Centrifugare. Asciugare in tumbler senza essiccare troppo. Finire stirando con abbondante vapore.

Lavabile in lavatrice

Easy care



Machine washable

Easy care

Il filato Cashwool® SWE raggiunge gli standard previsti da Woolmark per la marcatura "Total Easy Care" pertanto se il maglificio esegue una corretta tessitura, confezione e finissaggio secondo le indicazioni Woolmark è adatto a produrre maglieria "Total Easy Care".

Lavabile in lavatrice e asciugabile in tumbler

Total easy care



Machine washable and tumble dry

Total easy care

CASHWOOL® SWE

Nm. 2/30 - Nm. 2/48

100% (WV) EXTRAFINE WOOL



KNITTING

Nm. 2/30

F.F. Cotton 21-24 gg	Flat Machine 12-14	1 Ply
F.F. Cotton 12 gg	Flat Machine 7-8	2 Plies

Nm. 2/48

F.F. Cotton 27-30 gg	Flat Machine 14-16	1 Ply
F.F. Cotton 12 gg	Flat Machine 12	2 Plies

Optimum quantity: packages of about 24 kgs.

An extra charge will be required for packages of lighter weight.

Color fastness: as Woolmark standards.

Any special requests must be specified when ordering.

FINISHING

N.B. when using machine washable treated yarns it is necessary to knit tighter (increased cover factor) because during finishing generally no further consolidation of the knitting structure occurs.

Therefore, preliminary testing of knitting and finishing is necessary to verify that garments meet your expectation. Steam finishing and pressing is enough to achieve good appearance and quality. To highlight the softness and bulkiness of the yarn, a gentle wet finishing for about 3 minutes in 35°C water with 2-3% softener on the weight of the garments/panels is recommended. Hydro-extract and tumble-dry; garments should not be over-dried. Steam finish and press.

CASHWOOL SWE Nm. 2/30-2/48 - 100% (WV)



4

A

420812
M

B

026169

C

027216

D

442315
M

E

421423
M



5


027025

026911

027027

442677
M

027151



6

001254

008764

442483
M

008764

000527



7

8

9

A

027832

420665
M

421041
M

B

027273

443102
M

442622
M

C

027275

442196
M

027117

D

441477
M

442195
M

443352
M

E

027098

025752

026672



10

A

442621
M

B

027105

C

027122

D

027123

E

442688
M

11

421225
M

027097

118206

441702
M

027087

12

025518

027031

441410
M

025275

442255
M



13

14

15

A

420810
M

027236

027853

B

420986
M

027856

027237

C

441614
M

027841

027215

D

441269
M ●

027793 ●

027846

E

008800 ●

441706
M

441875
M



16



A

443349
M

B

441959
M

C

441250
M


D

441481
M

E

441259
M ●

17



420702
M

420588
M

420266
M ●

421428
M

420426
M ●

18



099054
●

420284
M ●

441142
M

420964
M ●

099070
●

INDEX

● 000527	6E	027031	12B	027841	14C	M 420939	1B	M 441614	13C
● 001205	2A	027087	11E	027846	15D	M ● 420964	18D	M 441702	11D
001254	6A	027097	11B	027853	15A	M 420986	13B	M 441706	14E
008764	6B	027098	7E	027856	14B	M 420991	1E	M 441875	15E
● 008768	6D	027105	10B	118206	11C	M 421041	9A	M 441882	2C
● 008800	13E	027117	9C	● 099054	18A	M 421225	11A	M 441959	16B
025146	2E	027122	10C	● 099070	18E	M 421423	4E	M 442195	8D
025275	12D	027123	10D	M ● 420266	17C	M ● 421425	1C	M 442196	8C
025518	12A	027151	5E	M ● 420284	18B	M 421428	17D	M 442255	12E
025628	E3	027215	15C	M ● 420426	17E	M ● 440988	1D	M 442315	4D
025752	8E	027216	4C	M ● 420573	1A	M 441142	18C	M 442483	6C
026169	4B	027236	14A	M 420588	17B	M 441250	16C	M 442621	10A
026672	9E	027237	15B	M 420665	8A	M ● 441259	16E	M 442622	9B
026900	3C	027273	7B	M 420702	17A	M ● 441269	13D	M 442677	5D
026911	5B	027275	7C	M 420810	13A	M 441316	2D	M 442688	10E
027024	3B	027280	3D	M 420812	4A	M 441410	12C	M 443102	8B
027025	5A	● 027793	14D	M ● 420819	2B	M 441477	7D	M 443349	16A
027027	5C	027832	7A	M 420938	3A	M 441481	16D	M 443352	9D

“●” Colori disponibili in CASHWOOL SWE Nm 2/48

“●” Available colours in CASHWOOL SWE Nm 2/48

“M”: melange

I seguenti colori, benché indicati come M “melange”, sono stati prodotti con tecnologia “supermelange”:
420266 – 420702 – 420939 – 421423 – 421425 – 421428

Following colours, despite they are marked as M “melange”, have been produced using “supermelange” technology:
420266 – 420702 – 420939 – 421423 – 421425 – 421428