

EVEREST

Nm. 4500
83% (WV) LANA
10% (WM) MOHAIR
7% (PA) POLIAMMIDE

IMPIEGO

Rett. Fin. 5 a 1 capo

FINISSAGGIO

La follatura è indispensabile per esaltare le caratteristiche del filo. Si consiglia un trattamento in acqua tiepida max 35°C con sapone neutro e/o ammorbidente al 2-3% sul peso merce. La durata del finissaggio dipende dal tipo di macchina e dal risultato desiderato.

Asciugare in tumbler avendo cura di non essiccare troppo i capi/teli. (max 70°C.) Stirare con abbondante vapore.

EVEREST

Nm. 4500
83% (WV) WOOL
10% (WM) MOHAIR
7% (PA) POLYAMIDE


KNITTING

Flat Machine Gauge 5 1 Ply

FINISHING

Milling is indispensable to highlight the yarn's characteristics. We recommend treatment in lukewarm water (max 35°C) With neutral soap and/or softener at 2-3% of the weight of the goods.

How long the finish lasts depends on the type of machine and desired results. Tumble-dry with care to avoid excessive drying of garments/cloth (max 70°C). Iron with lots of steam.



INDEX

660179	3E	660622	3A	661339	2F
660182	3D	660803	2D	661340	2E
660183	2A	660806	1F	661341	2C
660184	2B	660811	3F	661342	3C
660359	1E	660812	1D	661695	3B
660521	1B	660813	1A	661697	1C



Associazione Tessile e Salute

I nostri articoli soddisfano tutti i requisiti di Tessile e Salute.

Zegna Baruffa Lane Borgosesia partecipa al progetto Tessile e Salute finanziato dal Ministero della Salute.

www.tessileesalute.it

1

2

3

A



660813



660183



660622

B



660521



660184



661695

C



661697



661341



661342

D



660812



660803



660182

E



660359



661340



660179

F



660806



661339



660811