

1

2

3

4

5

6

A

852475

859576

852488

A

852485

852503

852481

B

852474

859578

852487

B

852492

852484

852480

C

852476

852489

852486

C

852504

852483

852479

D

852477

852490

852491

D

859593

852482

852478



7

8

9

A

852473

852499

852493

B

852497

852496

851675

C

852500

852498

852494

D

852501

852502

852495

CAMPIONE GRATUITO ESENTE DA BOLLATA DI ACCOMPAGNAMENTO (ART. 4 N. 6 D.P.R. N. 827 DEL 6-10-1978)

Must

SUPERGEELONG MOULINÉ NM. 2/15.000

100% (WV) lana baby merino extrafine



IMPIEGO

Rettilinea finezza 7 Cotton 12 1 Capo

FINISSAGGIO

Consigliamo di immergere i capi, a rovescio, in acqua con durezza inferiore a 5° francesi, PH 5.5, la cui temperatura non superi i 30° C. Il rapporto bagno sarà 20/1 (pari a 20 litri di acqua per ogni chilo di materiale).

Lavate con sapone frollante, risciacquate, scaricate l'acqua e lavate di nuovo con poco ammorbidente se lo ritenete necessario (non oltre l'1,5% sul peso dei capi, compatibilmente con il tipo di ammorbidente utilizzato).

Centrifugate un minuto o più, per eliminare tutta l'acqua. Estrarre subito e distendere bene le maglie per evitare di rendere le pieghe permanenti.

asciugate brevemente in tumbler ad una temperatura che non oltrepassi i 70°C.

Colori diversi necessitano tempi di frollatura diversi e pertanto non possono essere trattati congiuntamente; maglie di identico colore ma lavorate su macchine di diversa finezza devono essere frollate separatamente.

Poiché il risultato finale viene sensibilmente influenzato dalla fittezza del capo e dal tipo di materiale utilizzato, è necessario effettuare prove che determinino le tempistiche da adottare.

STOCK SERVICE

Il minimo ordinabile è di kg. 24 per colore. (scatola standard)

SOLIDITÀ COLORI

Rispondenti alle norme Woolmark.

Per uso in rigato con colori contrastanti richiedere solidità specifica per rigatura.

Must

SUPERGEELONG MOULINÉ NM. 2/15.000

100% (WV) extrafine baby merino wool



KNITTING

Flat machine 7 Cotton 12 1 Ply

FINISHING

We recommend to soak the garments on their reverse side in water, the hardness of which is equal or below 5° French, PH 5.5 and temperature not over 30°C. Bath ratio must be 20/1 (20 liters of water per kilogram of the garments).

Wash with milling soap, rinse, drain and wash again adding a small amount of softener, if you find it necessary (not over 1,5% on the weight of the garments, depending on the type of softener used).

Spin-dry the garments for one minute or more in order to reduce the amount of water.

Lay the garments flat to avoid creases.

Briefly tumble dry at 70°C max.

Different colours require different finishing time and cannot be washed together; garments having the same colour but being knitted on different gauge/needle must be washed separately.

The final result is very much affected by the stitch length and by the type of machine used; it is thus very important to test the duration of finishing, in order to achieve the expected handfeel.

STOCK SERVICE

The minimum quantity per order is 24 kgs. (standard box)

COLOURS FASTNESS

Woolmark standards.

In case of striped or contrast knitwear a specific dyeing fastness must be asked.



Per capi rigati lavare a secco
In case of striped knitwear drycleaning is recommended

INDEX

851675	9/B	852484	5/B	852496	8/B
852473	7/A	852485	4/A	852497	7/B
852474	1/B	852486	3/C	852498	8/C
852475	1/A	852487	3/B	852499	8/A
852476	1/C	852488	3/A	852500	7/C
852477	1/D	852489	2/C	852501	7/D
852478	6/D	852490	2/D	852502	8/D
852479	6/C	852491	3/D	852503	5/A
852480	6/B	852492	4/B	852504	4/C
852481	6/A	852493	9/A	859576	2/A
852482	5/D	852494	9/C	859578	2/B
852483	5/C	852495	9/D	859593	4/D



Associazione Tessile e Salute
I nostri articoli soddisfano tutti i requisiti di Tessile e Salute
Zigra Beaufa Lana Borgogna partner in progetto Tessile e Salute finanziato dal Ministero della Salute
www.tessilee salute.it