




Botto Poala®

GOLD
Nm 2/80

COMPOSIZIONE: 70% (WS) cashmere - 30% (SE) seta	COMPOSITION: 70% (WS) cashmere - 30% (SE) silk
CARATTERISTICHE: TIPO DI TINTURA: in tops e in matasse TIPOLOGIA: Filato pettinato NODI: Splicer CONFEZIONE: Rocche da kg 1 ca. PILLING (ISO 12945-1): 3/4	FEATURES: TYPE OF DYEING: tops dyed and hank dyed CONSTRUCTION: Worsted yarns KNOTS: Slicer PACKAGING: Cones of about 1kg PILLING (ISO 12945-1): 3/4
IMPIEGO: Rett. Fin. 18 - 21 Cotton 33 - 37 - 42 gg	USE: Flat machine 18 - 21 FF Cotton 33 - 37 - 42 gg
COLORI: Cartelle propria con selezione di colori Melange, Uniti e sablè . Si possono tingere colori a richiesta. I colori con effetto devono essere considerati a titolo indicativo, in quanto la loro riproduzione può variare a seconda della composizione del filo sul quale gli stessi vengono tinti. È bene pertanto tenere in considerazione che non siamo sempre in grado di garantire una perfetta e fedele riproduzione del colore rispetto al campione di riferimento.	COLOURS: Own colour card with selected Melange, solid and sablè colours. custom-made colours can be dyed. The sablè colors Gold and Dahlia have to be considered as an indication, as their reproduction can vary depending on the composition of the yarn on which they are dyed, please note that we are not always able to guarantee a perfect and faithful color reproduction.
QUANTITA' OTTIMALI: Colori a stock service: a partire da 1 kg, collo ideale kg 20 circa Colori uniti non a stock o al campione: kg. 6-9-12-16-24-30-40-60-73-100-150-300-600 Supplementi previsti dalle nostre condizioni generali di vendita	IDEAL QUANTITIES: Stock service colours: starting from 1 kg each, standard box approximately kg 20 No stock or custom solid colours: kg. 6-9-12-16-24-30-40-60-73-100-150-300-600 Extra charge according to our General Sales Conditions.
SOLIDITA': COMFORMITA' NORMATIVA REACH: si COMFORMITA' NORMATIVA GB 18401: si (Categoria B: prodotti a contatto diretto con la pelle)	FASTNESS: REACH REGULATION COMPLIANCE: yes GB 18401 REGULATION COMPLIANCE: yes (Category B products directly in contact with the skin)
PER RIGATURE: in caso di rigatura a forte contrasto richiedere solidità specifica	FOR STRIPES: in case of stripes with high contrast colors we suggest ,to ask for special color fastness
FINISSAGGIO: Consigliamo trattamento dei capi a rovescio come segue: effettuare un accurato prestiro rapporto bagno pari a 40 litri di acqua per ogni kg. di materiale lavare in acqua a 25/30°C con sapone per 2/3 minuti . Centrifugare 3/5 minuti a 800 giri Asciugare in tumbler a bassa temperatura, non completamente; estrarre i capi dall'essiccatoio ancora leggermente umidi. Stirare con poco vapore. È possibile effettuare il lavaggio dei capi a secco o a idrocarburi. Poiché il risultato finale viene sensibilmente influenzato dalla fittezza del capo e dal tipo di macchinario è necessario effettuare prove sulle tempistiche da adottare	FINISHING: We suggest the following finishing: Turn garments inside out Pre-press Bath ratio equal to 40 liters of water for 1 kg Wash in water at 25/30° with soap for 2/3 minutes Spin dry at 800 cycles for 3 to 5 minutes Tumble dry at low temperature, garments should be slightly wet when removed from the tumbler. Press with little steam It is possible to dry clean or with hydrocarbons Final result varies according to knitting and machinery, therefore it is suggested to perform several trials in order to achieve the requested result



STAGIONE **AUTUNNO-INVERNO 2017-18**

DATA RILASCIO: 20/5/2016


Documento Approvato



Botto Poala®

GOLD
Nm 3/80

COMPOSIZIONE: 70% (WS) cashmere - 30% (SE) seta	COMPOSITION: 70% (WS) cashmere - 30% (SE) silk
CARATTERISTICHE: TIPO DI TINTURA: in tops e in matasse TIPOLOGIA: Filato pettinato NODI: Splicer CONFEZIONE: Rocche da kg 1 ca. PILLING (ISO 12945-1): 3/4	FEATURES: TYPE OF DYEING: tops dyed and hank dyed CONSTRUCTION: Worsted yarns KNOTS: Slicer PACKAGING: Cones of about 1kg PILLING (ISO 12945-1): 3/4
IMPIEGO: Rett. Fin. 16 - 18 1 capo Cotton 30-33 gg 1 capo	USE: Flat machine 16 - 18 1 ply FF Cotton 30-33 gg 1 ply
COLORI: Cartelle propria ccon selezione di colori Melange, Uniti e sablé. Si possono tingere colori a richiesta. I colori con effetto sablé devono essere considerati a titolo indicativo, in quanto la loro riproduzione può variare a seconda della composizione del filo sul quale gli stessi vengono tinti. È bene pertanto tenere in considerazione che non siamo sempre in grado di garantire una perfetta e fedele riproduzione del colore rispetto al campione di riferimento.	COLOURS: Own colour card with selected Melange, Solid and Sablé colours. Custom-made colours can be dyed. The sablé colours have to be considered as an indication, as their reproduction can vary depending on the composition of the yarn on which they are dyed, please note that we are not always able to guarantee a perfect and faithful color reproduction.
QUANTITA' OTTIMALI: Colori a stock service: a partire da 1 kg, collo ideale kg 20 circa Colori uniti non a stock o al campione: kg. 6-9-12-16-24-30-40-60- 73-100-150-300-600 Supplementi previsti dalle nostre condizioni generali di vendita	IDEAL QUANTITIES: Stock service colours: starting from 1 kg each, standard box approximately kg 20 No stock or custom solid colours: kg. 6-9-12-16-24-30-40-60-73- 100-150-300-600 Extra charge according to our General Sales Conditions.
SOLIDITA': COMFORMITA' NORMATIVA REACH: si COMFORMITA' NORMATIVA GB 18401: si (Categoria B: prodotti a contatto diretto con la pelle)	FASTNESS: REACH REGULATION COMPLIANCE: yes GB 18401 REGULATION COMPLIANCE: yes (Category B products directly in contact with the skin)
PER RIGATURE: in caso di rigatura a forte contrasto richiedere solidità specifica	FOR STRIPES: in case of stripes with high contrast colors we suggest ,to ask for special color fastness
FINISSAGGIO: Consigliamo trattamento dei capi a rovescio come segue: effettuare un accurato prestiro rapporto bagno pari a 40 litri di acqua per ogni kg. di materiale lavare in acqua a 25/30°C con sapone per 2/3 minuti . Centrifugare 3/5 minuti a 800 giri Asciugare in tumbler a bassa temperatura, non completamente; estrarre i capi dall'essiccatoio ancora leggermente umidi. Stirare con poco vapore. È possibile effettuare il lavaggio dei capi a secco o a idrocarburi. Poiché il risultato finale viene sensibilmente influenzato dalla finezza del capo e dal tipo di macchinario è necessario effettuare prove sulle tempistiche da adottare	FINISHING: We suggest the following finishing: Turn garments inside out Pre-press Bath ratio equal to 40 liters of water for 1 kg Wash in water at 25/30°with soap for 2/3 minutes Spin dry at 800 cycles for 3 to 5 minutes Tumble dry at low temperature, garments should be slightly wet when removed from the tumbler. Press with little steam It is possible to dry clean or with hydrocarbons Final result varies according to knitting and machinery, therefore it is suggested to perform several trials in order to achieve the requested result



STAGIONE AUTUNNO-INVERNO 2017-18

DATA RILASCIO: 20/5/2016

Documento Approvato