



MILLENNIUM

Nm 2/60


Botta Poala


SUPER 120'S
YARN CERTIFIED BY WOODMARK
WORLD CODE OF PRACTICES 2112


PURE NEW WOOL



COMPOSIZIONE: 100% lana merino ultrafine 120'S

COMPOSITION: 100% ultrafine merino wool 120'S

CARATTERISTICHE:

TIPO DI TINTURA: in tops e in matasse
TIPOLOGIA: Filato pettinato
NODI: Splicer
CONFEZIONE: Rocche da kg 1 ca.
PILLING (ISO 12945-1 (7200 giri): 3/4

FEATURES:

TYPE OF DYEING: tops dyed and hank dyed
CONSTRUCTION: Worsted yarns
KNOTS: Splicer
PACKAGING: Cones of about 1kg
PILLING (ISO 12945-1 (twist 7200): 3/4

IMPIEGO:

Rett. Fin. 16-18 1 capo
Cotton 30-33 gg 1 capo

USE:

Flat machine 16-18 1ply
FF Cotton 30-33 gg 1ply

COLORI:

Cartelle propria. Mélange, super mélanges e Uniti stock service
Si possono tingere colori uniti a richiesta.

COLOURS:

Own colour card. Mélange, super mélanges and solid colours
stock service
Custom-made solid colour can be dyed.

QUANTITA' OTTIMALI:

Colori pronti: a partire da 1 kg, collo ideale kg 24 circa
Colori uniti bco e candeggiati: kg. 6-9-12-16-24-30-40-60-73-100-
150-300-600
Colori uniti o al campione: kg 6-9-12-16-24-33-40-50-60-73-84-
100-150-168-300-336-600-670
Supplementi previsti come da nostre condizioni generali di vendita

IDEAL QUANTITIES:

Available colours: starting from 1 kg each, standard box
approximately kg 24
Colours white and bleached: kg. 6-9-12-16-24-30-40-60-73-100-
150-300-600
Solid custom colors: kg 6-9-13-16-24-33-40-50-60-73-84-100-150-
168-300-336-600-670
Extra charge according to our General Sales Conditions.

SOLIDITA':

CONFORMITA' NORMATIVA REACH: si
CONFORMITA' NORMATIVA GB 18401: si
(Categoria B: prodotti a contatto diretto con la pelle)
**In caso di rigatura a forte contrasto, richiedere specifiche
all'atto dell'ordine**

FASTNESS:


REACH REGULATION COMPLIANCE: yes
GB 18401 REGULATION COMPLIANCE: yes
(Category B products directly in contact with the skin)
**In case of stripes with high contrast pls ask for specifications
when ordering**

FINISSAGGIO:

Consigliamo trattamento dei capi a rovescio come segue:
effettuare un accurato prestiro
rapporto bagno pari a 40 litri di acqua per ogni kg. di materiale
lavare in acqua a 25/30°C con ammorbidente per 2/3 minuti.
Centrifugare 3/5 minuti a 800 giri
Asciugare in tumbler a bassa temperatura, non completamente;
estrarre i capi dall'essiccatoio ancora leggermente umidi.
Stirare con poco vapore.
E' possibile effettuare il lavaggio dei capi a secco o a idrocarburi.
Poiché il risultato finale viene sensibilmente influenzato dalla
finezza del capo e dal tipo di macchinario è necessario effettuare
prove sulle tempistiche da adottare

FINISHING:

We suggest the following finishing:
Turn garments inside out
Pre-press
Bath ratio equal to 40 liters of water for 1 kg
Wash in water at 25/30° with softener for 2/3 minutes
Spin dry at 800 cycles for 3 to 5 minutes
Tumble dry at low temperature, garments should be slightly wet
when removed from the tumbler.
Press with little steam
It is possible to dry clean or with hydrocarbons
Final result varies according to knitting and machinery, therefore it
is suggested to perform several trials in order to achieve the
requested result



STAGIONE AUTUNNO-INVERNO 2021/22

DATA RILASCIO: 03/06/2020



MILLENNIUM

Nm 2/80

Botta Poala

SUPER 120'S
YARN CERTIFIED BY WOOLMARK

PURE NEW WOOL

SUPERMÉLANGE
COLOUR

COMPOSIZIONE: 100% (WV) lana merino ultrafine 120'S

COMPOSITION: 100%(WV) ultrafine merino wool 120'S

CARATTERISTICHE:

TIPO DI TINTURA: in tops e in matasse
TIPOLOGIA: Filato pettinato
NODI: Splicer
CONFEZIONE: Rocche da kg 1 ca.
PILLING (ISO 12945-1 (7200 giri): 3/4

FEATURES:

TYPE OF DYEING: tops dyed and hank dyed
CONSTRUCTION: Worsted yarns
KNOTS: Splicer
PACKAGING: Cones of about 1kg
PILLING (ISO 12945-1 (twist 7200): 3/4

IMPIEGO:

Rett. Fin. 18-21 1 capo
Cotton 33-37-42 gg 1 capo

USE:

Flat machine 18-21 1ply
FF Cotton 33-37-42 gg 1ply

COLORI:

Cartelle propria con selezione di colori mélange, super mélanges e Uniti
Si possono tingere colori uniti a richiesta.

COLOURS:

Own colour card with selected mélange, super mélanges and solid colours
Custom-made solid colour can be dyed.

QUANTITA' OTTIMALI:

Colori pronti: a partire da 1 kg, collo ideale kg 24 circa
Colori uniti bco e candeggiati: kg. 6-9-12-16-24-30-40-60-73-100-150-300-600
Colori uniti o al campione: kg 6-9-12-16-24-33-40-50-60-73-84-100-150-168-300-336-600-670
Supplementi previsti come da nostre condizioni generali di vendita

IDEAL QUANTITIES:

Available colours: starting from 1 kg each, standard box approximately kg 24
Colours white and bleached: kg. 6-9-12-16-24-30-40-60-73-100-150-300-600
Solid custom colors: kg 6-9-13-16-24-33-40-50-60-73-84-100-150-168-300-336-600-670
Extra charge according to our General Sales Conditions.

SOLIDITA':

CONFORMITA' NORMATIVA REACH: si
CONFORMITA' NORMATIVA GB 18401: si
(Categoria B: prodotti a contatto diretto con la pelle)
In caso di rigatura a forte contrasto, richiedere specifiche all'atto dell'ordine

FASTNESS:

REACH REGULATION COMPLIANCE: yes
GB 18401 REGULATION COMPLIANCE: yes
(Category B products directly in contact with the skin)
In case of stripes with high contrast pls ask for specifications when ordering

FINISSAGGIO:

Consigliamo trattamento dei capi a rovescio come segue:
effettuare un accurato prestiro
rapporto bagno pari a 40 litri di acqua per ogni kg. di materiale
lavare in acqua a 25/30°C con ammorbidente per 2/3 minuti.
Centrifugare 3/5 minuti a 800 giri
Asciugare in tumbler a bassa temperatura, non completamente;
estrarre i capi dall'essiccatoio ancora leggermente umidi.
Stirare con poco vapore.
È possibile effettuare il lavaggio dei capi a secco o a idrocarburi.
Poiché il risultato finale viene sensibilmente influenzato dalla fittezza del capo e dal tipo di macchinario è necessario effettuare prove sulle tempistiche da adottare

FINISHING:

We suggest the following finishing:
Turn garments inside out
Pre-press
Bath ratio equal to 40 liters of water for 1 kg
Wash in water at 25/30° with softener for 2/3 minutes
Spin dry at 800 cycles for 3 to 5 minutes
Tumble dry at low temperature, garments should be slightly wet when removed from the tumbler.
Press with little steam
It is possible to dry clean or with hydrocarbons
Final result varies according to knitting and machinery, therefore it is suggested to perform several trials in order to achieve the requested result



STAGIONE AUTUNNO-INVERNO 2021/22

DATA RILASCIO: 03/06/2020