WOOL and

Z67231-Z67234

Nm 2/48 Tex 20,8x2

COMPOSIZIONE	COMPOSITION
60% (WV) lanaextra fine 40% (PA) poliammide	60% (WV) extrafine wool 40% (PA) polyamide
COLORI	**COLOURS**
Si possono tingere colori uniti a richiesta. *I colori da noi forniti hanno valori di solidità secondo quanto previsto da Woolmark. Questi valori non garantiscono l'utilizzo in rigato, specialmente per i forti contrasti. Eventuali esigenze particolari dovranno essere specificate all'atto dell'ordine.* **Sono necessarie prove preventive di tessitura e finissaggio per verificare che i capi soddisfino i requisiti richiesti.**	Custom solid colours can be dyed upon request. *Our colour fastness values meet Woolmark standards.* *Some colours may not be suitable for striped or contrast knitting. In this case a specific dye fastness must be expressly requested.* **Preliminary testing on knitting and finishing is necessary to verify that garments meet requirements.**
QUANTITA' OTTIMALI	**IDEAL QUANTITIES**
Colori uniti a richiesta: Kg. 9-18-30-45-70-100-160-320-630 Supplementi: saranno applicati come previsto dalle nostre condizioni generali di vendita.	Solid custom colours: Kg. 9-18-30-45-70-100-160-320-630 Surcharges: will be added according to our general sales conditions.
CARATTERISTICHE	**FEATURES**
In questo filato particolarmente morbido e confortevole - Easy Care, dalle interessanti proprietà legate al concetto della termoregolazione - lana e poliammide convivono, dando origine ad un filo dinamico e contemporaneo. Ideale per realizzare maglie eleganti e active	In this particularly soft and comfort yarn – Easy Care, having interesting properties related to the concept of thermostatic temperature control – wool and polyamide coexist, giving origin to a dynamic and contemporary yarn. Ideal to produce elegant and active garments.
IMPIEGO	**USE**
Rett. Fin. 14 — 1 capo Cotton 24 – 27 gg — 1 capo	Flat machine 14 — 1 ply FF Cotton 24 – 27 gg — 1 ply
FINISSAGGIO	**FINISHING**
Consigliamo trattamento dei capi a rovescio come segue: effettuare un accurato prestiro rapporto bagno pari a 40 litri di acqua per ogni kg. di materiale lavare in acqua a 25/30℃ con ammorbidente per 2/3 minuti. Centrifugare 3/5 minuti a 800 giri Asciugare in tumbler a bassa temperatura, non completamente; estrarre i capi dall'essiccatoio ancora leggermente umidi. Stirare con poco vapore. E' possibile effettuare il lavaggio dei capi a secco o a idrocarburi. Poiché il risultato finale viene sensibilmente influenzato dalla fittezza del capo e dal tipo di macchinario utilizzato, è necessario effettuare prove sulle tempistiche da adottare	We suggest the following finishing: Turn garments inside out Pre-press Bath ratio equal to 40 liters of water for 1 kg Wash in water at 25/30° with softner for 2/3 minut es Spin dry at 800 cycles for 3 to 5 minutes Tumble dry at low temperature, garments should be slightly wet when removed from the tumbler. Press with little steam It is possible to dry clean or with hydrocarbons Final result varies according to knitting and machinery, therefore it is suggested to perform several trials in order to achieve the requested result
ETICHETTATURA	**LABELLING**

LAVABILE IN LAVATRICE) – EASY CARE - (MACHINE WASHABLE)

Il filato WOOL and ha superato gli standard previsti da WOOLMARK per la marcatura "TOTAL EASY CARE", pertanto è adatto a produrre maglieria "TOTAL EASY CARE" se il maglificio esegue una corretta tessitura, confezione e finissaggio secondo le indicazioni WOOLMARK. La garanzia "TOTAL EASY CARE" prevede la specifica richiesta all'atto dell'ordine.

WOOL and yarn meets WOOLMARK standards for "TOTAL EASY CARE" labelling, therefore it is suited to produce "TOTAL EASY CARE" garments if the knitting factory ensures proper knitting, linking and finishing,as per WOOLMARK instructions. The "TOTAL EASY CARE" guarantee must be specifically requested when ordering.

(lavabile in lavatrice e asciugabile in tumbler) – TOTAL EASY CARE - (Machine washable and tumble dry)

STAGIONE: AUTUNNO INVERNO 2016/17 — **Documento Approvato**

DATA RILASCIO: **22/06/2015**