DRAGON
Nm 2x2/120

COMPOSIZIONE: 100% (SE) seta	***COMPOSITION: 100% (SE) silk***
CARATTERISTICHE: TIPO DI TINTURA: in tops e in matasse TIPOLOGIA: Filato pettinato NODI: Splicer CONFEZIONE: Rocche da kg 1 ca. PILLING (ISO 12945-1 (7200 giri): 3/4	***FEATURES:*** *TYPE OF DYEING: tops dyed and hank dyed* *CONSTRUCTION: Worsted yarns* *KNOTS: Splicer* *PACKAGING: Cones of about 1kg* *PILLING* (ISO 12945-1 (*twist 7200*): *3/4*
IMPIEGO: Rett. Fin. 16-18 — 1 capo Cotton 30 - 33 gg — 1 capo	***USE:*** *Flat machine 16-18* — *1ply* *FF Cotton 30-33 gg* — *1ply*
COLORI: Cartella propria con selezione di colori uniti Colori melange: stock service Si possono tingere colori uniti a richiesta.	***COLOURS:*** *Own colour card with selected solid colors* *Melange colors: stock service,* *Custom-made colors can be dyed.*
QUANTITA' OTTIMALI: colori pronti a partire da 1 kg, collo ideale kg 20 circa Mélange: colli da Kg.24 circa. È possibile produrre quantità da kg. 6-12-16-24-36-48-55-60-72-100-120-132-144-156 supplementi previsti dalle nostre condizioni generali di vendita	***IDEAL QUANTITIES:*** *Available colours: starting from 1 kg each, standard box approximately kg 20* *Mélange colours: Box of approx. 24 Kg* *6-12-16-24-36-48-55-60-72-100-120-132-144-156 kg lots can be dyed.* *surcharge will be asked according to our General Sales Conditions.*
SOLIDITA': CONFORMITA' NORMATIVA REACH: si CONFORMITA' NORMATIVA GB 18401: si (Categoria B: prodotti a contatto diretto con la pelle) **PER RIGATURE: in caso di rigatura a forte contrasto richiedere solidità specifica**	***FASTNESS:*** *REACH REGUALATION COMPLIANCE: yes* *GB 18401 REGULATION COMPLIANCE: yes* *(Category B products directly in contact with the skin)* ***FOR STRIPES: in case of stripes with high contrast colors we suggest ,to ask for special color fastness***
FINISSAGGIO: Consigliamo trattamento dei capi a rovescio come segue: effettuare un accurato prestiro rapporto bagno pari a 40 litri di acqua per ogni kg. di materiale lavare in acqua a 25/30℃ con sapone per 1/2 minuti . Centrifugare 3/5 minuti a 800 giri Asciugare in tumbler a bassa temperatura, non completamente; estrarre i capi dall'essiccatoio ancora leggermente umidi. Stirare con poco vapore. È possibile effettuare il lavaggio dei capi a secco o a idrocarburi. Poiché il risultato finale viene sensibilmente influenzato dalla fittezza del capo e dal tipo di macchinario è necessario effettuare prove sulle tempistiche da adottare	***FINISHING:*** *We suggest the following finishing:* *Turn garments inside out* *Pre-press* *Bath ratio equal to 40 liters of water for 1 kg* *Wash in water at 25/30°with soap for 1/2 minutes* *Spin dry at 800 cycles for 3 to 5 minutes* *Tumble dry at low temperature, garments should be slightly wet when removed from the tumbler.* *Press with little steam* *It is possible to dry clean or with hydrocarbons* *Final result varies according to knitting and machinery, therefore it is suggested to perform several trials in order to achieve the requested result*



STAGIONE AUTUNNO-INVERNO 2018/19

DATA RILASCIO: 05/06/2017