




RAJA

Nm 2/48



COMPOSIZIONE: 70%(WV) Lana Merino superfine 30%(WS) Cashmere	COMPOSITION: 70%(WV) Superfine Merino Wool 30%(WS) Cashmere
CARATTERISTICHE: TIPO DI TINTURA: In fiocco o in matasse TIPOLOGIA: Filato Cardato NODI: Splicer CONFEZIONE Rocche da kg 1 ca. PILLING: (ISO 12945-1 (7200 giri): 3	FEATURES: <i>TYPE OF DYEING: Fiber dyed or hank dyed</i> <i>CONSTRUCTION: Woolen yarns</i> <i>KNOTS: Splicer</i> <i>PACKAGING: Cones of about 1kg</i> <i>PILLING (ISO 12945-1 (twist 7200): 3</i>
IMPIEGO: Rett. F. 14 Cotton 24/27 gg	USE: Flat machine F. 14 Cotton 24/27 gg
COLORI: Cartella propria con selezione di colori in stock service	COLOURS: <i>Own shade card with selected colours in stock service</i>
QUANTITA' OTTIMALI: Colori stock service: a partire da 1 kg. Colli da circa kg.20 Colori non stock service: uniti tinti in matasse, kg. 6-16-30-36-48-55-63-84-125-250. Tinti in fiocco kg.120 minimo. Supplementi: saranno applicati come previsto dalle nostre condizioni generali di vendita.	IDEAL QUANTITIES: <i>Stock service colors: from 1 kg. up.</i> <i>Cartons of approx. Kg.20.</i> <i>Non stock service colors:</i> <i>Hank dyed solid shades, kg. 6-16-30-36-48-55-63-84-125-250.</i> <i>Fiber dyed, 120 kg. minimum</i> <i>Surcharge: will be added according to our general sales conditions.</i>
SOLIDITA': CONFORMITA' NORMATIVA REACH: si CONFORMITA' NORMATIVA GB 18401: si (Categoria B: prodotti a contatto diretto con la pelle)	FASTNESS: <i>REACH REGULATION COMPLIANCE: yes</i> <i>GB 18401 REGULATION COMPLIANCE: yes</i> <i>(Category B products directly in contact with the skin)</i>
PER RIGATURE: in caso di rigatura a forte contrasto richiedere solidità specifica	FOR STRIPES: in case of stripes with high contrast colors we suggest to ask for special color fastness
FINISSAGGIO: Consigliamo trattamento dei capi a rovescio come segue: rapporto bagno pari a 30 litri di acqua per ogni kg. di materiale lavare in acqua a 35/40° con sapone per 1/2 minuti centrifugare 1/2 minuti a 800 giri lavare a 35/40° con ammorbidente per 3/5 minuti centrifugare 5/8 minuti a 800 giri asciugare in tumbler a 70/80° stirare con molto vapore Poiché il risultato finale viene sensibilmente influenzato dalla fittezza del capo e dal tipo di macchinario utilizzato, è necessario effettuare prove sulle tempistiche da adottare.	FINISHING: <i>We suggest the following finishing:</i> <i>Turn garments inside out</i> <i>Bath ratio equal to 30 liters of water for 1 kg</i> <i>Wash in water at 35/40° with soap for 1/2 minutes</i> <i>Spin dry at 800 cycles for 1 to 2 minutes</i> <i>Wash at 35/40° with softener for 3/5 minutes</i> <i>Spin dry at 800 cycles for 5 to 8 minutes</i> <i>Tumble dry at 70/80°</i> <i>Press with generous steam</i> <i>Final result varies according to knitting and machinery, therefore it is suggested to perform several trials in order to achieve the requested result</i>
ETICHETTATURA 	
STAGIONE AUTUNNO-INVERNO 2018/19	DATA RILASCIO: 05/06/2017