SUPERGEELONG MOULINE

Nm 2/15

COMPOSIZIONE: 100% (WV) Lana Baby Merino Extrafine	***COMPOSITION:*** *100%(WV) Extrafine Baby Merino Wool*
CARATTERISTICHE: TIPO DI TINTURA: In fiocco o in matasse TIPOLOGIA: Filato Cardato NODI: Splicer CONFEZIONE: Rocche da kg 1 ca. PILLING (ISO 12945-1 (7200 giri): 3	***FEATURES:*** *TYPE OF DYEING: Fiber dyed or hank dyed* *CONSTRUCTION: Woolen yarns* *KNOTS: Splicer* *PACKAGING: Cones of about 1kg* *PILLING* (ISO 12945-1 (*twist 7200*): *3*
IMPIEGO: Nm 2/15 Rett. Fin. 7 1 capo Si consiglia di lavorare a due o più guidafili	***USE:*** *Nm 1/15 Flat machine F. 7 1 ply* *We recommend to knit using more than one threadguide*
COLORI: Stock sevice: tutti i colori sono disponibili Oltre ai colori di cartella, possono essere realizzate altre combinazioni attingendo alla cartella Supergeelong	***COLOURS:*** *Stock service: all colors are available* *In addition to the colors displayed in our color card, other combinations can be made, choosing from our Supergeelong color card*
QUANTITA' OTTIMALI: Multipli di kg. 2 Supplementi: saranno applicati come previsto dalle nostre condizioni generali di vendita.	***IDEAL QUANTITIES:*** *Multiples of kgs. 2* *Surcharge: will be added according to our general sales conditions.*
SOLIDITA': CONFORMITA' NORMATIVA REACH: si CONFORMITA' NORMATIVA GB 18401: si (Categoria B: prodotti a contatto diretto con la pelle) **PER RIGATURE: in caso di rigatura a forte contrasto richiedere solidità specifica**	***FASTNESS:*** *REACH REGUALATION COMPLIANCE: yes* *GB 18401 REGULATION COMPLIANCE: yes* *(Category B products directly in contact with the skin)* ***FOR STRIPES: in case of stripes with high contrast colors we suggest ,to ask for special color fastness***
FINISSAGGIO: Consigliamo trattamento dei capi a rovescio come segue: rapporto bagno pari a 30 litri di acqua per ogni kg. di materiale lavare in acqua a 35/40°con sapone per 1/2 minuti centrifugare 1/2 minuti a 800 giri lavare a 35/40°con ammorbidente per 2/4 minuti centrifugare 5/8 minuti a 800 giri asciugare in tumbler a 70/80° stirare con molto vapore Poiché il risultato finale viene sensibilmente influenzato dalla fittezza del capo e dal tipo di macchinario utilizzato, è necessario effettuare prove sulle tempistiche da adottare.	***FINISHING:*** *We suggest the following finishing:* *Turn garments inside out* *Bath ratio equal to 30 liters of water for 1 kg* *Wash in water at 35/40°with soap for 1/2 minutes* *Spin dry at 800 cycles for 1 to 2 minutes* *Wash at 35/40°with softener for 2/4 minutes* *Spin dry at 800 cycles for 5 to 8 minutes* *Tumble dry at 70/80°* *Press with generous steam* *Final result varies according to knitting and machinery, therefore it is suggested to perform several trials in order to achieve the requested result*

ETICHETTATURA



STAGIONE **AUTUNNO-INVERNO 2018/19**

DATA RILASCIO: **05/06/2017**