




# AKITA

Nm 1/12.000



<b>COMPOSIZIONE:</b> 80% (WV) Lana Merino superfine 20%(WS) Cashmere	<b>COMPOSITION:</b> 80%(WV) Superfine Merino Wool 20%(WS) Cashmere
<b>CARATTERISTICHE:</b> TIPO DI TINTURA: In fiocco o in matasse TIPOLOGIA: Filato Cardato NODI: Splicer CONFEZIONE: Rocche da kg 1 ca. PILLING (ISO 12945-1 (7200 giri): 3	<b>FEATURES:</b> TYPE OF DYEING: Fiber dyed or hank dyed CONSTRUCTION: Woolen yarns KNOTS: Splicer PACKAGING: Cones of about 1kg PILLING (ISO 12945-1 (twist 7200): 3
<b>IMPIEGO:</b> Rett. Fin 12 1 capo Cotton 21-24 gg 1 capo	<b>USE:</b> Flat machine 12 1 ply F F Cotton 21-24 gg 1 ply
<b>COLORI:</b> Cartella propria con selezione di colori in stock service	<b>COLOURS:</b> Own shade card with selected colours in stock service
<b>QUANTITA' OTTIMALI:</b> Colori stock service: a partire da 1 kg. Colli da circa kg.20 Colori a campione o non stock service: tinti in matasse, kg. 6-16-30-36-48-55-63-84-125-250.  Supplementi: saranno applicati come previsto dalle nostre condizioni generali di vendita.	<b>IDEAL QUANTITIES:</b> Stock service colors: starting from 1 kg. each Cartons of approx. Kg.20 Custom or no stock service colors: Hank dyed solid shades, kg. 6-16-30-36-48-55-63-84-125-250.  Surcharge: will be added according to our general sales conditions.
<b>SOLIDITA':</b> CONFORMITA' NORMATIVA REACH: si CONFORMITA' NORMATIVA GB 18401: si (Categoria B: prodotti a contatto diretto con la pelle)	<b>FASTNESS:</b> REACH REGULATION COMPLIANCE: yes GB 18401 REGULATION COMPLIANCE: yes (Category B products directly in contact with the skin)
<b>PER RIGATURE:</b> in caso di rigatura a forte contrasto richiedere solidità specifica	<b>FOR STRIPES:</b> in case of stripes with high contrast colors we suggest ,to ask for special color fastness
<b>FINISSAGGIO:</b> Consigliamo trattamento dei capi a rovescio come segue: rapporto bagno pari a 30 litri di acqua per ogni kg. di materiale lavare in acqua a 35/40° con sapone per 1/2 minuti centrifugare 1/2 minuti a 800 giri lavare a 35/40° con ammorbidente per 3/5 minuti centrifugare 5/8 minuti a 800 giri asciugare in tumbler a 70/80° stirare con molto vapore Poiché il risultato finale viene sensibilmente influenzato dalla fittezza del capo e dal tipo di macchinario utilizzato, è necessario effettuare prove sulle tempistiche da adottare.	<b>FINISHING:</b> We suggest the following finishing: Turn garments inside out Bath ratio equal to 30 liters of water for 1 kg Wash in water at 35/40° with soap for 1/2 minutes Spin dry at 800 cycles for 1 to 2 minutes Wash at 35/40° with softener for 3/5 minutes Spin dry at 800 cycles for 5 to 8 minutes Tumble dry at 70/80° Press with generous steam Final result varies according to knitting and machinery, therefore it is suggested to perform several trials in order to achieve the requested result
<b>ETICHETTATURA</b> 	
<b>STAGIONE AUTUNNO-INVERNO 2019/20</b>	
<b>DATA RILASCIO: 05/06/2018</b>	