



GELSOMINO

ZH05861

Nm.24000 Tex.71.42

COMPOSIZIONE 64% (LI) lino 36% (VI) viscosa	COMPOSITION 64% (LI) linen 36% (VI) viscose
COLORI Propria cartella colori uniti. Si possono tingere colori uniti a richiesta.	COLOURS Own solid colours card. Custom solid colours can be dyed upon request
QUANTITA' OTTIMALI E' possibile produrre bagni da kg 6-12-16-24-36-48-55-60-72-100-120-132-144-250 con i supplementi previsti dalle nostre condizioni generali di vendita.	IDEAL QUANTITIES 6-12-16-24-36-48-55-60-72-100-120-132-144-250kg lots can be dyed; a surcharge will be asked according to our General Sales Conditions.
CARATTERISTICHE Filato pettinato NODI: Splicer CONFEZIONE: Rocche da kg 1 Il lino per sua stessa natura presenta peculiarità del tutto speciali; potrebbe manifestare differenza di colore fra le partite di greggio, dando origine a scarsa uniformità di tonalità fra le forniture. Data la speciale composizione di questo filato, non tutti i toni possono essere riprodotti fedelmente. In alcuni casi, è possibile che si manifesti un leggero effetto melange. Una superficie leggermente irregolare è caratteristica propria del lino. A causa della sua naturale "rigidità", inoltre, il lino può evidenziare spirality nella maglia rasata dopo il lavaggio in acqua. Sono quindi necessarie prove preventive di tessitura e finissaggio per verificare che i capi possiedano i requisiti richiesti	FEATURES Worsted yarn KNOTS: Splicer PACKAGING: Cones of about 1 kg <i>Linen, by its very nature, reveals very special peculiarities; the colour of raw white yarn can vary from lot to lot and therefore cause slight colour difference among the lots supplied. Due to the yarn special composition, then, it may be difficult to exactly reproduce all requested shades. Occasionally a slight melange effect may appear. A delicately uneven surface is one of linen's peculiarities. In addition, due to linen natural "stiffness", spirality may appear on plain jersey when washed in water. Preliminary testing on knitting and finishing is necessary to be sure that the garments meet your requirements</i>
IMPIEGO Rett. Fin. 14 - 16 1 capo FF Cotton 27-30-33 1 capo	USE Flat machine 14 - 16 1ply FF Cotton 27-30-33 1 ply
FINISSAGGIO Consigliamo trattamento dei capi a rovescio come segue: effettuare un accurato prestiro rapporto bagno pari a 40 litri di acqua per ogni kg. di materiale lavare in acqua a 25/30°C con ammorbidente per 2/3 minuti. Centrifugare 3/5 minuti a 800 giri Asciugare in tumbler a bassa temperatura, non completamente; estrarre i capi dall'essiccatoio ancora leggermente umidi. Stirare con poco vapore. E' possibile effettuare il lavaggio dei capi a secco o a idrocarburi. Poiché il risultato finale viene sensibilmente influenzato dalla fittezza del capo e dal tipo di macchinario utilizzato, è necessario effettuare prove sulle tempistiche da adottare	FINISHING <i>We suggest the following finishing:</i> <i>Turn garments inside out</i> <i>Pre-press</i> <i>Bath ratio equal to 40 liters of water for 1 kg</i> <i>Wash in water at 25/30° with softner for 2/3 minut es</i> <i>Spin dry at 800 cycles for 3 to 5 minutes</i> <i>Tumble dry at low temperature, garments should be slightly wet when removed from the tumbler.</i> <i>Press with little steam</i> <i>It is possible to dry clean or with hydrocarbons</i> <i>Final result varies according to knitting and machinery, therefore it is suggested to perform several trials in order to achieve the requested result</i>
ETICHETTATURA	LABELLING
STAGIONE PRIMAVERA ESTATE 2017	Documento Approvato
DATA RILASCIO: 04/01/2016	