Botto Poala®

SIRIO silver - SIRIO gold

ZP66011 – ZP66041

Nm.32000 Tex.31,25

COMPOSIZIONE	***COMPOSITION***
84% (WV) lana super extrafine 120'S (17,5 Micron) 9%(PA) poliammide 7%(PL) poliestere metallizzato lurex	*84% (WV) 120'S super extra fine wool (17,5 Micron)* *9%(PA) polyamide* *7%(PL) polyester metalized lurex*
COLORI	***COLOURS***
cartella illustrativa colori uniti. Si possono tingere colori uniti a richiesta. È importante notare che, a parità di codice, l'effetto del colore cambia notevolmente a seconda dell'articolo sul quale viene tinto, anche a causa del riflesso caldo o freddo del metallo. Consigliamo di chiedere una prova di laboratorio per i colori non presenti in cartella.	*Illustrative solid colours card. Customer's solid colours can by dyed upon request. We wish to point out that the visual perception of a colour- the colour code being equal- very much varies depending on the type of yarn on which it is dyed, due to the warm or cool metal reflection. It is advisable to ask for a lab-dip to be dyed if you wish to order a colour which is not included in colours card.*
QUANTITA' OTTIMALI	***IDEAL QUANTITIES***
Colori a stock service: a partire da 1 kg, collo ideale kg 24 circa E' possibile produrre bagni da kg 6-9-16-24-30-40-60-73-100-150-300-600. con i supplementi previsti dalle nostre condizioni generali di vendita.	*Stock service colours: starting from 1 kg each, standard box approximately kg 24* *6-9-16-24-30-40-60-73-100-150-300-600kg lots are available on request at extra charge according to our General Sales Conditions.*
CARATTERISTICHE	***FEATURES***
Filato pettinato NODI: Splicer CONFEZIONE: Rocche da kg 1	*Worsted yarn* *KNOTS: Splicer* *PACKAGING: Cones of about 1 kg*
IMPIEGO	***USE***
Rett. Fin. 16-18 1 capo Cotton 30 - 33 gg 1 capo	*Flat machine 16-18 1 ply* *FF Cotton 30 - 33 gg 1 ply*
FINISSAGGIO	***FINISHING***
Consigliamo trattamento dei capi a rovescio come segue: effettuare un accurato prestiro rapporto bagno pari a 40 litri di acqua per ogni kg. di materiale lavare in acqua a 25/30℃ con ammorbidente per 2/3 minuti. Centrifugare 3/5 minuti a 800 giri Asciugare in tumbler a bassa temperatura, non completamente; estrarre i capi dall'essiccatoio ancora leggermente umidi. Stirare con poco vapore. E' possibile effettuare il lavaggio dei capi a secco o a idrocarburi. Poiché il risultato finale viene sensibilmente influenzato dalla fittezza del capo e dal tipo di macchinario utilizzato, è necessario effettuare prove sulle tempistiche da adottare	*We suggest the following finishing:* *Turn garments inside out* *Pre-press* *Bath ratio equal to 40 liters of water for 1 kg* *Wash in water at 25/30°with softner for 2/3 minut es* *Spin dry at 800 cycles for 3 to 5 minutes* *Tumble dry at low temperature, garments should be slightly wet when removed from the tumbler.* *Press with little steam* *It is possible to dry clean or with hydrocarbons* *Final result varies according to knitting and machinery, therefore it is suggested to perform several trials in order to achieve the requested result*
ETICHETTATURA	***LABELLING***



STAGIONE: PRIMAVERA - ESTATE 2017

Documento Approvato

DATA RILASCIO: 04/01/2016