



Botto Poala

5 CONTINENTS

ZP06071

Nm 2/80 Tex 12,5X2

COMPOSIZIONE 100%(CO) cotone ELS (Extra Long Staple)	COMPOSITION 100%(CO) ELS cotton (Extra Long Staple)
COLORI Vedere propria cartella illustrativa colori uniti. Si possono tingere colori uniti a richiesta.	COLOURS See own illustrative solid colour card. Custom solid colours can be dyed upon request.
QUANTITA' OTTIMALI Colori stock service: a partire da kg. 1, collo ideale da Kg.20 circa. E' possibile produrre quantità da kg.6-12-16-24-36-48-55-60-72-100-120-132-144-250 con i supplementi previsti dalle nostre condizioni generali di vendita	IDEAL QUANTITIES Stock service colours: starting from 1 kg. each, standard box approximately Kgs.20. 6-12-16-24-36-48-55-60-72-100-120-132-144-250 lots can be dyed; a surcharge will be asked according to our General Sales Conditions.
CARATTERISTICHE Filato pettinato NODI: Splicer CONFEZIONE: Rocche da kg 1	FEATURES Worsted yarn KNOTS: Splicer PACKAGING: Cones of about 1 kg
IMPIEGO Rett. Fin. 18-21 Cotton 33-37-42 gg	USE Flat machine 18 Cotton 33-37-42 gg
FINISSAGGIO Consigliamo trattamento dei capi a rovescio come segue: effettuare un accurato prestiro rapporto bagno pari a 40 litri di acqua per ogni kg. di materiale lavare in acqua a 25/30°C con ammorbidente per 2/3 minuti. Centrifugare 3/5 minuti a 800 giri Asciugare in tumbler a bassa temperatura, non completamente; estrarre i capi dall'essiccatoio ancora leggermente umidi. Stirare con poco vapore. E' possibile effettuare il lavaggio dei capi a secco o a idrocarburi. Poiché il risultato finale viene sensibilmente influenzato dalla fittezza del capo e dal tipo di macchinario utilizzato, è necessario effettuare prove sulle tempistiche da adottare	FINISHING We suggest the following finishing: Turn garments inside out Pre-press Bath ratio equal to 40 liters of water for 1 kg Wash in water at 25/30°with softner for 2/3 minut es Spin dry at 800 cycles for 3 to 5 minutes Tumble dry at low temperature, garments should be slightly wet when removed from the tumbler. Press with little steam It is possible to dry clean or with hydrocarbons Final result varies according to knitting and machinery, therefore it is suggested to perform several trials in order to achieve the requested result
ETICHETTATURA	LABELLING
STAGIONE: PRIMAVERA ESTATE 2017	Documento Approvato
DATA RILASCIO: 04/01/2016	



Botto Poala

5 CONTINENTS

ZP06072

Nm 3/80 Tex 12,5X3

COMPOSIZIONE 100%(CO) cotone ELS (Extra Long Staple)	COMPOSITION 100%(CO) ELS cotton (Extra Long Staple)
COLORI Vedere propria cartella illustrativa colori uniti. Si possono tingere colori uniti a richiesta.	COLOURS See own illustrative solid colour card. Custom solid colours can be dyed upon request.
QUANTITA' OTTIMALI Stock service colours: starting from 1 kg. each, standard box approximately Kgs.20. E' possibile produrre quantità da kg. 6-12-16-24-36-48-55-60-72-100-120-132-144-250 con i supplementi previsti dalle nostre condizioni generali di vendita	IDEAL QUANTITIES Stock service colours: starting from 1 kg. each, standard box approximately Kgs.20. 6-12-16-24-36-48-55-60-72-100-120-132-144-250 kg lots can be dyed; a surcharge will be asked according to our General Sales Conditions.
CARATTERISTICHE Filato pettinato NODI: Splicer CONFEZIONE: Rocche da kg 1	FEATURES Worsted yarn KNOTS: Splicer PACKAGING: Cones of about 1 kg
IMPIEGO Rett. Fin. 16 - 18 Cotton 30-33 gg	USE Flat machine 16 - 18 FF Cotton 30-33 gg
FINISSAGGIO Consigliamo trattamento dei capi a rovescio come segue: effettuare un accurato prestiro rapporto bagno pari a 40 litri di acqua per ogni kg. di materiale lavare in acqua a 25/30°C con ammorbidente per 2/3 minuti. Centrifugare 3/5 minuti a 800 giri Asciugare in tumbler a bassa temperatura, non completamente; estrarre i capi dall'essiccatoio ancora leggermente umidi. Stirare con poco vapore. E' possibile effettuare il lavaggio dei capi a secco o a idrocarburi. Poiché il risultato finale viene sensibilmente influenzato dalla fittezza del capo e dal tipo di macchinario utilizzato, è necessario effettuare prove sulle tempistiche da adottare	FINISHING We suggest the following finishing: Turn garments inside out Pre-press Bath ratio equal to 40 liters of water for 1 kg Wash in water at 25/30°with softner for 2/3 minut es Spin dry at 800 cycles for 3 to 5 minutes Tumble dry at low temperature, garments should be slightly wet when removed from the tumbler. Press with little steam It is possible to dry clean or with hydrocarbons Final result varies according to knitting and machinery, therefore it is suggested to perform several trials in order to achieve the requested result
ETICHETTATURA	LABELLING
STAGIONE: PRIMAVERA ESTATE 2017	Documento Approvato
DATA RILASCIO: 04/01/2016	