



# CASHWOOL SWE

Nm 2/30



<b>COMPOSIZIONE:</b> 100% (WV) lana merino extrafine	<b>COMPOSITION:</b> 100% (WV) extrafine merino wool
<b>CARATTERISTICHE:</b> TIPO DI TINTURA: in tops e in matasse TIPOLOGIA: Filato pettinato NODI: Splicer CONFEZIONE: Rocche da kg 1 ca. PILLING (ISO 12945-1 (7200 giri): 3	<b>FEATURES:</b> TYPE OF DYEING: tops dyed and hank dyed CONSTRUCTION: Worsted yarns KNOTS: Slicer PACKAGING: Cones of about 1 kg PILLING (ISO 12945-1 (twist 7200): 3
<b>IMPIEGO:</b> Rett. Fin. 12-14 1 capo FF Cotton 21-24-27 gg 1 capo	<b>USE:</b> Flat machine 12-14 1 ply FF Cotton 21-24-27 gg 1 ply
<b>COLORI:</b> Melange super melange e uniti: cartella propria con stock service. Si possono tingere colori uniti a richiesta.	<b>COLOURS:</b> Melange, super melange and solid colors: own stock service colors card. Custom solid colors can be dyed upon request.
<b>QUANTITA' OTTIMALI:</b> Colli da 24 Kg. circa. Colori uniti a richiesta: Kg 9-18-30-45-70-100-160-320-630. Supplementi: saranno applicati come previsto dalle nostre condizioni generali di vendita.	<b>IDEAL QUANTITIES:</b> Cartons of approx. 24 Kg Solid custom colors: Kg 9-18-30-45- 70-100-160-320-630. Surcharges: will be added according to our general sales conditions.
<b>SOLIDITA':</b> COMFORMITA' NORMATIVA REACH: si COMFORMITA' NORMATIVA GB 18401: si (Categoria B: prodotti a contatto diretto con la pelle)	<b>FASTNESS:</b> REACH REGULATION COMPLIANCE: yes GB 18401 REGULATION COMPLIANCE: yes (Category B products directly in contact with the skin)
<b>PER RIGATURE:</b> in caso di rigatura a forte contrasto richiedere solidità specifica	<b>FOR STRIPES:</b> in case of stripes with high contrast colors we suggest to ask for special color fastness
<b>FINISSAGGIO:</b> Consigliamo trattamento dei capi a rovescio come segue: effettuare un accurato prestiro rapporto bagno pari a 40 litri di acqua per ogni kg. di materiale lavare in acqua a 25/30°C con ammorbidente per 2/3 minuti. Centrifugare 3/5 minuti a 800 giri Asciugare in tumbler a bassa temperatura, non completamente; estrarre i capi dall'essiccatoio ancora leggermente umidi. Stirare con poco vapore. È possibile effettuare il lavaggio dei capi a secco o a idrocarburi. Poiché il risultato finale viene sensibilmente influenzato dalla fittezza del capo e dal tipo di macchinario è necessario effettuare prove sulle tempistiche da adottare	<b>FINISHING:</b> We suggest the following finishing: Turn garments inside out Pre-press Bath ratio equal to 40 liters of water for 1 kg Wash in water at 25/30° with softener for 2/3 minutes Spin dry at 800 cycles for 3 to 5 minutes Tumble dry at low temperature, garments should be slightly wet when removed from the tumbler. Press with little steam It is possible to dry clean or with hydrocarbons Final result varies according to knitting and machinery, therefore it is suggested to perform several trials in order to achieve the requested result


## ETICHETTATURA



(LAVABILE IN LAVATRICE) – EASY CARE - (MACHINE WASHABLE)

Il filato CASHWOOL /SWE ha superato gli standard previsti da WOOLMARK per la marcatura "TOTAL EASY CARE", pertanto è adatto a produrre maglieria "TOTAL EASY CARE" se il maglificio esegue una corretta tessitura, confezione e finissaggio secondo le indicazioni WOOLMARK.

CASHWOOL /SWE yarn meets WOOLMARK standards for "TOTAL EASY CARE" labelling, therefore it is suitable to produce "TOTAL EASY CARE" garments if the knitting factory ensures proper knitting, linking and finishing as per WOOLMARK instructions.



(lavabile in lavatrice e asciugabile in tumbler) – TOTAL EASY CARE - (Machine washable and tumble dry)

STAGIONE PRIMAVERA –ESTATE 2018

Documento Approvato

DATA RILASCIO: 13/01/2017

