



# H2DRY<sup>®</sup>

## K-CASHMERE

Nm 2/80

[www.h2dry.it](http://www.h2dry.it)



**COMPOSIZIONE:** 50% (WV) extrafine merino wool 140'S  
50% (WS) cashmere

**COMPOSITION:** 50%(WV) extrafine merino wool 140'S  
50% (WS) cashmere

**CARATTERISTICHE:**

TIPO DI TINTURA: in tops e in matasse  
TIPOLOGIA: Filato pettinato  
NODI: Splicer  
CONFEZIONE: Rocche da kg 1 ca.  
PILLING (ISO 12945-1 (7200 giri): 3

**FEATURES:**

TYPE OF DYEING: tops dyed and hank dyed  
CONSTRUCTION: Worsted yarns  
KNOTS: Slicer  
PACKAGING: Cones of about 1kg  
PILLING (ISO 12945-1 (twist 7200): 3

**IMPIEGO:**

Rett. Fin. 18-21                                 1 capo  
Cotton 33-37-42 gg                               1 capo

**USE:**

Flat machine 18 -21                                 1ply  
FF Cotton 33-37-42 gg                               1ply

**COLORI:**

Cartelle propria con selezione di colori Melange, Supermelange e  
Uniti.  
Si possono tingere colori a richiesta.

**COLOURS:**

Own colour card with selected melange, Supermelange and Solid  
colours.  
Custom-made colours can be dyed.

**QUANTITA' OTTIMALI:**

Colori a stock service: a partire da 1 kg, collo ideale kg 24 circa  
Colori uniti non a stock o al campione: kg. 6 - 9 - 16 - 24 - 30 - 40 -  
60 - 73 - 100 - 150 - 300  
Supplementi previsti dalle nostre condizioni generali di vendita.

**IDEAL QUANTITIES:**

Stock service colours: starting from 1 kg each, standard box  
approximately kg 24  
No stock or custom solid colours: kg. 6 - 9 - 16 - 24 - 30 - 40 - 60 -  
73 - 100 - 150 - 300  
Extra charge according to our General Sales Conditions.

**SOLIDITA':**

COMFORMITA' NORMATIVA REACH: si  
COMFORMITA' NORMATIVA GB 18401: si  
(Categoria B: prodotti a contatto diretto con la pelle)

**FASTNESS:**

REACH REGULATION COMPLIANCE: yes  
GB 18401 REGULATION COMPLIANCE: yes  
(Category B products directly in contact with the skin)

**PER RIGATURE: in caso di rigatura a forte contrasto  
richiedere solidità specifica**


**FOR STRIPES: in case of stripes with high contrast colors we  
suggest ,to ask for special color fastness**

**FINISSAGGIO:**

Consigliamo trattamento dei capi a rovescio come segue:  
effettuare un accurato prestiro  
rapporto bagno pari a 40 litri di acqua per ogni kg. di materiale  
lavare in acqua a 25/30°C con sapone per 2/3 minuti .  
**Sconsigliamo l'utilizzo di ammorbidenti silconici**  
Centrifugare 3/5 minuti a 800 giri  
Asciugare in tumbler a bassa temperatura, non completamente;  
estrarre i capi dall'essiccatoio ancora leggermente umidi.  
Stirare con poco vapore.  
È possibile effettuare il lavaggio dei capi a secco o a idrocarburi.  
Poiché il risultato finale viene sensibilmente influenzato dalla  
finezza del capo e dal tipo di macchinario è necessario effettuare  
prove sulle tempistiche da adottare

**FINISHING:**

We suggest the following finishing:  
Turn garments inside out  
Pre-press  
Bath ratio equal to 40 liters of water for 1 kg  
Wash in water at 25/30° with soap for 2/3 minutes  
**We suggest to avoid silicone based softeners**  
Spin dry at 800 cycles for 3 to 5 minutes  
Tumble dry at low temperature, garments should be slightly wet  
when removed from the tumbler.  
Press with little steam  
It is possible to dry clean or with hydrocarbons  
Final result varies according to knitting and machinery, therefore it  
is suggested to perform several trials in order to achieve the  
requested result



LAVABILE IN LAVATRICE (40°) – EASY CARE - (MACHINE WASHABLE)

STAGIONE **PRIMAVERA – ESTATE 2018**

Documento Approvato

DATA RILASCIO: 13/01/2017

