MAZATLAN
Nm 2/50

COMPOSIZIONE: 65% (SE) seta-35% (LI) lino	***COMPOSITION:*** *65% (SE) silk-35% (LI) linen*
CARATTERISTICHE: TIPO DI TINTURA: in matasse TIPOLOGIA: Filato pettinato NODI: Splicer CONFEZIONE: Rocche da kg 1 ca. PILLING (ISO 12945-1 (7200 giri): 3/4 Data la particolare mista ed il diverso assorbimento del colore da parte delle fibre che la compongono alcuni colori (nero e blu in particolare) potrebbero risultare meno saturi del previsto. In tal caso si tratterebbe di una caratteristica intrinseca del filato steso, non di un problema qualitativo.	***FEATURES:*** *TYPE OF DYEING: hank dyed* *CONSTRUCTION: Worsted yarns* *KNOTS: Slicer* *PACKAGING: Cones of about 1kg* *PILLING* (ISO 12945-1 (*twist 7200*)*: 3/4* *Considering the distinctive blend and the different dye absorption or the fibers, some colors (black and navy in particular) may appear less satured than expected. That should be considered as an attribute of the yarn, not as a quality issue.*
IMPIEGO: Rett. Fin. 14-16 1 capo FF cotton 27-30-33 1 capo	***USE:*** *Flat machine 14-16 1 ply* *FF cotton 27-30-33 1 ply*
COLORI: Cartella propria con colori uniti. Si possono tingere colori uniti a richiesta.	***COLOURS:*** *Specific colour card for solid colours. Custom-made solid colours can be dyed.*
QUANTITA' OTTIMALI: Colori disponibili a partire da 1 kg, collo ideale kg 20 circa Colori uniti kg. 6-12-16-24-36-48-55-60-72-100-120-132-144-156 Supplementi: previsti dalle nostre condizioni generali di vendita	***IDEAL QUANTITIES:*** *Available colours: starting from 1 kg each, standard box approximately kg 20* *solid colours:* *6-12-16-24-36-48-55-60-72-100-120-132-144-156 kg* *Surcharge: will be asked according to our General Sales Conditions.*
SOLIDITA': **A causa della composizione del filato le solidità GB 18401 (Cina) non sono garantite.** Questi valori non garantiscono l'utilizzo in rigato, specialmente per i forti contrasti. Eventuali esigenze particolari dovranno essere specificate all'atto dell'ordine.	***FASTNESS:*** ***Due to the yarn composition the GB 18401 (Cina) are not guaranteed.*** *Some colours might not be suitable for knitting stripes or other knitted pattern if using very contrasting colours. Any other special fastness should be expressly requested.*
FINISSAGGIO: Consigliamo trattamento dei capi a rovescio come segue: effettuare un accurato prestiro rapporto bagno pari a 40 litri di acqua per ogni kg. di materiale lavare in acqua a 25/30℃ con sapone per 1/2 minuti . Centrifugare 3/5 minuti a 800 giri Asciugare in tumbler a bassa temperatura, non completamente; estrarre i capi dall'essiccatoio ancora leggermente umidi. Stirare con poco vapore. È possibile effettuare il lavaggio dei capi a secco o a idrocarburi. Poiché il risultato finale viene sensibilmente influenzato dalla fittezza del capo e dal tipo di macchinario è necessario effettuare prove sulle tempistiche da adottare	***FINISHING:*** *We suggest the following finishing:* *Turn garments inside out* *Pre-press* *Bath ratio equal to 40 liters of water for 1 kg* *Wash in water at 25/30°with soap for 1/2 minutes* *Spin dry at 800 cycles for 3 to 5 minutes* *Tumble dry at low temperature, garments should be slightly wet when removed from the tumbler.* *Press with little steam* *It is possible to dry clean or with hydrocarbons* *Final result varies according to knitting and machinery, therefore it is suggested to perform several trials in order to achieve the requested result*



STAGIONE PRIMAVERA – ESTATE 2018

DATA RILASCIO: 13/01/2017

Documento Approvato