

## BRITTANY NM. 2/45.000

100% (WV) lana merino superfine (17,5 micron)

### IMPIEGO

F.F. Cotton 24 - 27 gg, Rettilinea finezza 14 1 Capo



## BEGONIA NM. 2/48.000

80% (WV) lana merino superfine (15,5 micron)  
20% (SE) seta

### IMPIEGO

F.F. Cotton 24 - 27 gg, Rettilinea finezza 14 1 Capo



### FINISSAGGIO

Consigliamo di immergere i capi, a rovescio, in acqua con durezza inferiore a 5° francesi, PH 5.5, la cui temperatura non superi i 30° C. Il rapporto bagno sarà 20/1 (pari a 20 litri di acqua per ogni chilo di materiale).

Lavate con sapone follante, risciacquate, scaricate l'acqua e lavate di nuovo con poco ammorbidente se lo ritenete necessario (non oltre l'1,5% sul peso dei capi, compatibilmente con il tipo di ammorbidente utilizzato).

Centrifugate un minuto o più, per eliminare tutta l'acqua.

Estrarre subito e distendere bene le maglie per evitare di rendere le pieghe permanenti.

Asciugate brevemente in tumbler ad una temperatura che non oltrepassi i 70°C.

Colori diversi necessitano tempi di follatura diversi e pertanto non possono essere trattati congiuntamente; maglie di identico colore ma lavorate su macchine di diversa finezza devono essere folgate separatamente.

Poiché il risultato finale viene sensibilmente influenzato dalla fittezza del capo e dal tipo di materiale utilizzato, è necessario effettuare prove che determinino le tempistiche da adottare.

### SOLIDITÀ COLORI

Rispondenti alle norme Woolmark.

Per uso in rigato con colori contrastanti richiedere solidità specifica per rigatura.

## BRITTANY NM. 2/45.000

100% (WV) superfine merino wool (17,5 micron)

### KNITTING

F.F. Cotton 24 - 27 gg, Flat machine 14 1 Ply



## BEGONIA NM. 2/48.000

80% (WV) superfine merino wool (15,5 micron)  
20% (SE) silk

### KNITTING

F.F. Cotton 24 - 27 gg, Flat machine 14 1 Ply



### FINISHING

We recommend to soak the garments on their reverse side in water, the hardness of which is equal or below 5° french, PH 5.5 and temperature not over 30°C. Bath ratio must be 20/1 (20 liters of water per kilogram of garments).

Wash with milling soap, rinse, drain and wash again adding a small amount of softener, if you like it (not over 1,5% on the garment weight, depending on the type of softener used).

Spin-dry the garments for one minute or more in order to reduce the amount of water.

Lay the garments flat in order to avoid creases.

Tumble dry briefly at 70°C max.

Different colours require different finishing time and cannot be washed together; garments having the same colour but being knitted on different gauge/needle must be washed separately.

The final result is very much affected by the stitch length and by the type of machine used; it is thus very important to test the duration of finishing, in order to achieve the expected handfeel.

### COLOURS FASTNESS

Woolmark standards.

In case of striped or contrast knitwear a specific dyeing fastness must be asked.



1

2

3

A



\* 203610



● 840902



● 200124

B



\* 201988



● 840873  
*Melange*



● 852015  
*Melange*

C



● 840813  
*Melange*



● 840899  
*Melange*



● 852016  
*Melange*

D



● 841945  
*Melange*



● 841837  
*Melange*



● 840848  
*Melange*

E



851264  
*Melange*



202011



201989

4

5

6

A



● 851249  
*Melange*




028147



850835

B



028108



028110



028214

C



● 841375  
*Melange*



● 201188



028150

D



● 027295



● 201105



209309

E



841497  
*Melange*



● 200023



● 841781  
*Melange*



A



● 841303  
*Melange*

B



●\* 027838

C




● 841310  
*Melange*

D



● 841700  
*Melange*

E



● 849622  
*Melange*



● 841993  
*Melange*




208376



●\* 008800



● 849405  
*Melange*



●\* 200480




● 840927  
*Melange*



● 840602  
*Melange*



● 841420  
*Melange*



● 840312  
*Melange*



● 840357  
*Melange*

## INDEX

●*	008800	11/C		208376	11/B	Melange	841497	4/E
●	027295	4/D		209309	6/D	Melange	● 841658	8/A
	027721	7/B		209310	7/A	Melange	● 841700	10/D
●*	027838	10/B		726063	8/E	Melange	● 841781	6/E
	028108	4/B	●	781051	7/C	Melange	● 841837	2/D
	028110	5/B	Melange	● 840312	12/D	Melange	841896	9/D
	028147	5/A	Melange	● 840357	12/E	Melange	● 841945	1/D
	028150	6/C	Melange	840492	7/D	Melange	● 841993	11/A
	028191	8/B	Melange	● 840602	12B	Melange	● 849405	11/D
	028214	6/B	Melange	● 840790	8/D	Melange	● 849622	10/E
	028229	9/A	Melange	● 840813	1/C		● 849659	8/C
●	200023	5/E	Melange	● 840848	3/D		● 849660	7/E
●	200124	3/A	Melange	● 840873	2/B		● 849663	9/E
●*	200480	11/E		● 840899	2/C		850835	6/A
●	201105	5/D		● 840902	2/A		● 850881	9/B
●	201188	5/C	Melange	● 840927	12/A		● 850905	9/C
*	201988	1/B	Melange	● 841303	10/A	Melange	● 851249	4/A
	201989	3/E	Melange	● 841310	10/C	Melange	851264	1/E
	202011	2/E	Melange	● 841375	4/C	Melange	● 852015	3/B
*	203610	1/A	Melange	● 841420	12/C	Melange	● 852016	3/C

● Brittany: Colori disponibili / Available colours

\* Begonia: Colori disponibili / Available colours