



**MIRTO**  
ZH02491  
Nm 9500  
Tex 105,2

<b>COMPOSIZIONE</b> 78%(WS) Cashmere Ultra Fine 22%(PA) Poliammide	<b>COMPOSITION</b> 78%(WS) Ultra Fine Cashmere 22%(PA) Polyamide
<b>COLORI</b> Cartella illustrative di colori uniti. Si possono tingere colori uniti a richiesta. <i>I colori da noi forniti hanno valori di solidita' secondo quanto previsto da Woolmark. Questi valori non garantiscono l'utilizzo in rigato, specialmente per i forti contrasti. Eventuali esigenze particolari dovranno essere specificate all'atto dell'ordine.</i>	<b>COLOURS</b> Illustrative solid colour card. Solid Custom-made colours can be dyed. <i>We guarantee that for every colour we dye, the colour fastness values are as per woolmark standard. Some colours might not be suitable for knitting stripes or other knitted pattern if using very contrasting colours. Any other special fastness should be expressly requested.</i>
<b>QUANTITA' OTTIMALI</b> Kg. 6-9-16-30-40-60-90-130 vengono applicati sovrapprezzi secondo le nostre condizioni generali di vendita.	<b>IDEAL QUANTITIES</b> Kg. 6-9-16-30-40-60-90-130 An extra charge will be requested according to our General Sales Conditions.
<b>CARATTERISTICHE</b> Questo prodotto nasce dall'unione di una materia prima esclusiva, <i>Cashmere</i> ultrafine, e dalla nostra tecnologia di filatura Mousse. Il prodotto ottenuto è estremamente soffice e leggero.	<b>FEATURES</b> This product is the result of an exclusive fiber like ultrafine cashmere and the spinning-technique known as 'Mousse'. The resulting yarn is an extremely light soft fancy yarn
<b>IMPIEGO</b> Rett. E. 7-8 1-capo	<b>USE</b> Flat machine E.7-8 1-ply
<b>FINISSAGGIO</b> La follatura è indispensabile per esaltare le caratteristiche del filo. Si consiglia un trattamento in acqua tiepida 30°-35 °C con sapone neutro e/o ammorbidente al 2-3 % sul peso merce. La durata del finissaggio dipende dal tipo di macchina e dal risultato desiderato. Asciugare in tumbler avendo cura di non essiccare troppo. Finire stirando con abbondante vapore.	<b>FINISHING</b> Milling is necessary to enhance yarn features and softness. We recommend a gentle wet finishing in lukewarm water 30°- 35°C containing 2-3% of soap and/or softener on goods' weight. Processing time depends on type of machine and result desired. Dry in tumbler. Do not over-dry . Finish giving generous steam.
<b>ETICHETTATURA</b>	<b>LABELLING</b>



STAGIONE AUTUNNO-INVERNO 2013-2014

Documento Approvato

DATA RILASCIO: 13/06/2012