



TEDDY

Z41331

Nm 1600 Tex 625

COMPOSIZIONE 61% (WV) lana 35% (WP) alpaca 4%(PA) poliammide	COMPOSITION 61% (WV) wool 35% (WP) alpaca 4%(PA) polyamide
COLORI Cartella illustrativa di colori uniti. Si possono tingere colori uniti a richiesta. <i>I colori da noi forniti hanno valori di solidità secondo quanto previsto da Woolmark. Questi valori non garantiscono l'utilizzo in rigato, specialmente per i forti contrasti. Eventuali esigenze particolari dovranno essere specificate all'atto dell'ordine.</i>	COLOURS Illustrative solid colour card. Solid Custom-made colours can be dyed. <i>We guarantee that for every colour we dye, the colour fastness values are as per woolmark standard. Some colours might not be suitable for knitting stripes or other knitted pattern if using very contrasting colours. Any other special fastness should be expressly requested.</i>
QUANTITA' OTTIMALI Colori uniti Kg 65-85-125-250. E' possibile produrre quantità di 6-16-30-40 kg con i supplementi previsti dalle nostre condizioni generali di vendita	IDEAL QUANTITIES Solid colours kg 65-85-125-250. 6-16-30-40 kg lots are available on request at extra charge according to our General Sales conditions
CARATTERISTICHE Filato bouclé, la maglia come pelliccia.	FEATURES Bouclé yarn, the knit like a fur.
IMPIEGO Rett. Fin. 1,5 1 capo Per ottenere buoni risultati è necessario operare con le tensioni dei guidafili al minimo possibile, regolando la chiusura della maglia in modo da non sollecitare troppo il filato.	USE Flat machine 1,5 1 ply To obtain best results knit using lowest tension of yarn-guides. Find machine regulation that does not pull the yarn too much during knitting.
FINISSAGGIO Si consiglia una breve follatura 2-3 minuti in acqua tiepida 35°C con ammorbidente. Finire stirando con abbondante vapore.	FINISHING A short milling for 2-3 min. In warm water at 35°C with softener is recommended. Give generous steam
ETICHETTATURA	LABELLING
STAGIONE: AUTUNNO-INVERNO 2013-2014	Documento Approvato
DATA RILASCIO: 15/02/13	