MOU

ZP40372

Nm 3300 Tex 303x1

COMPOSIZIONE	**COMPOSITION**
80%(WS) Cashmere 20%(SE) Seta	80%(WS) Cashmere 20%(SE) Silk
COLORI	**COLOURS**
Cartella illustrativa colori uniti. Si possono tingere colori uniti a richiesta previa approvazione del relativo lab-dip. *I colori da noi forniti hanno valori di solidita' secondo quanto previsto da Woolmark. Questi valori non garantiscono l'utilizzo in rigato, specialmente per i forti contrasti. Eventuali esigenze particolari dovranno essere specificate all'atto dell'ordine.*	Illustrative colour card for solid colours. Custom solid colour can be dyed upon request, after lab-dip approval. *Our colour fastness values meet Woolmark standards.* *Some colour may not be suitable for striped or contrast knitting.* *In this case a specific dye fastness must be espressly requested.*
QUANTITA' OTTIMALI	**IDEAL QUANTITIES**
Colori tinti in matasse: Kg. 6-16-30-40-65-85-125-250. Supplementi previsti come da nostre condizioni generali di vendita.	Hank dyed colours: Kg. 6-16-30-40-65-85-125-250. Surcharge according to our General Sales Conditions.
CARATTERISTICHE	**FEATURES**
La lavorazione fantasia di cashmere ultrafine dà origine ad un bouclé lussuoso e morbidissimo per realizzare maglieria di pregio assoluto.	The fancy spinning of the finest cashmere gives rise to a luxury and ultrasoft bouclé, suitable to produce knitwear of absolute preciousness.
IMPIEGO	**USE**
Rett. Fin. 5 1-capo	Flat machine 5 1-ply
FINISSAGGIO	**FINISHING**
Per evidenziare le caratteristiche di pregio di questo filato consigliamo: - Trattamento di follatura in acqua a 35°C con ammo rbidente per un tempo di 5/6 minuti. - Centrifuga. - Asciugatura naturale dei capi in piano. - Stiro con vaporizzo su pressa dei capi non perfettamente asciutti **Sono necessarie prove preventive di tessitura e finissaggio per verificare che i capi soddisfino i requisiti richiesti.**	Milling is necessary in order to highlight the luxury prestigious features of this yarn, we recommend: - Mill in water at 35°C with softener for 5-6 min. - Spin dry - Place the garments flat. - Keep them slightly wet and press using a heated place. **Preliminary testing on knitting and finishing is necessary to verify that garments meet requirements.**
ETICHETTATURA	**LABELLING**



STAGIONE AUTUNNO-INVERNO 2014-2015

DATA RILASCIO: 24/06/2014

Documento Approvato