



WELLINGTON

Z65751

Nm 2/44 Tex 22,7x2

COMPOSIZIONE 100% (WV) Lana Extrafine (19,5 Micron) Merino New Zealand	COMPOSITION 100% (WV) Extrafine Wool (19,5 Micron) Merino New Zealand
COLORI Si possono tingere colori uniti a richiesta. <i>I colori da noi forniti hanno valori di solidità secondo quanto previsto da Woolmark. Questi valori non garantiscono l'utilizzo in rigato, specialmente per i forti contrasti. Eventuali esigenze particolari dovranno essere specificate all'atto dell'ordine.</i>	COLOURS Customer's solid colour can be dyed upon request. <i>We guarantee that for every colour we dye, the colour fastness values are as per woolmark standard. Some colours might not be suitable for knitting stripes or other knitted pattern if using very contrasting colours. Any other special fastness should be expressly requested.</i>
QUANTITA' OTTIMALI Colori uniti a richiesta: Kg. 60-70-100-120-150-300-600. E' possibile produrre bagni da kg 6-9-16-24-30-40 con i supplementi previsti dalle nostre condizioni generali di vendita.	IDEAL QUANTITIES Solid custom-made colours: Kg. 60-70-100-120-150-300-600. 6-9-16-24-30-40 kg lots are available on request at extra charge according to our General Sales Conditions.
CARATTERISTICHE Il filato è realizzato con lane neozelandesi. La fibra si distingue per la sua particolare pulizia e per il suo grado di bianco. E' una lana particolarmente pregiata perché rara e prodotta solo in alcune fattorie dove, produttori esperti si tramandano la conoscenza e la cultura legata alla selezione manuale della fibra di generazione in generazione. Può essere definito come HIGH PERFORMANCE YARN, Il trattamento eseguito rende il filato idrorepellente e ne aumenta il potere antimacchia. Queste caratteristiche restano inalterate anche dopo 15 lavaggi, ad umido o a secco.	FEATURES The yarn is made by New Zealand wool. The fibre stands out for its special whiteness and cleanliness. It is an especially prized wool because it is rare and produced only on a very few farms, where expert growers hand down from generation to generation the knowledge and culture tied to the manual selection of the fibre. It can be defined as HIGH PERFORMANCE YARN, water and stain proof resistant. These characteristics remain intact even after 15 washes, whether the garment is washed in water or dry cleaned.
IMPIEGO Rett. Fin. 14 FF Cotton 24gg 1 capo	USE Flat machine 14 FF Cotton 24gg 1 ply
FINISSAGGIO Con un semplice stiro con abbondante vaporizzo si ottiene un ottimo aspetto della maglia. Per esaltare al meglio la sofficià e la gonfiezza del filato si consiglia una leggera follatura in acqua per 3-5 minuti con ammorbidente al 2-3% sul peso merce, ad una temperatura non superiore a 35°C. Centrifugare. Asciugare in tumbler avendo cura di non essiccare troppo. Finire stirando con abbondante vapore.	FINISHING A normal pressing with a lot of steam will give an excellent regular aspect. To enhance softness and bulkiness of the yarn, we suggest a light milling for 3-5 minutes in water using a wool-softener in ratio of 2-3% of the garments' weight, at a temperature of less than 35°C. Centrifuge. Tumble-dry without over-drying. Steam-press thoroughly.
ETICHETTATURA	LABELLING

STAGIONE: PRIMAVERA ESTATE 2014

DATA RILASCIO: 25/02/13

Documento Approvato

