

MEMPHIS Nm. 25000 - 51% (LI) 49% (CO) - VENERE Nm. 2/29 - 100% (LI)

	1	2	3
A	 290762	 027922	 027917
B	 027565	 290810	 290820
C	 290812	 290813	 290773
D	 290768	 290815	 290149 ▲
E	 027911	 290779	 290816

	4	5	6
A	099054 ● ▲	290782	290821 ●
B	001205 ● ▲	205915	290811
C	026865	027563	290814
D	205832	290767	290785 ● ▲
E	205836	290817	099070 ● ▲

MEMPHIS

Nm. 25000
51% (LI) LINO
49% (CO) COTONE

IMPIEGO

Rett. Fin. 14 a 1 capo

VENERE

Nm. 2/29
100% (LI) LINO

IMPIEGO

Rett. Fin. 12 a 1 capo

FINISSAGGIO

Per ottenere una buona stabilità dimensionale e una mano più morbida consigliamo di follare i teli o i capi in acqua tiepida con 2 gr./lt. di ammorbidente, quindi centrifugare ed asciugare in tumbler senza eccedere nell'essiccazione. Finire stirando con abbondante vapore.

NOTA

Segnaliamo che il lino, fibra naturale, presenta una disuniformità di base (colore del greggio non sempre uguale a sé stesso) che potrebbe essere origine di differenze di tonalità fra le forniture. Inoltre a causa della sua naturale "rigidità", il lino può evidenziare spirality nella maglia rasata dopo il lavaggio in acqua.

La riproduzione dei colori può variare tingendo articoli di composizione differente. Vi preghiamo pertanto di prestare attenzione al materiale in cui è realizzata la cartella – Memphis, eccetto colore 290149 e colore 026865 in Venere – e di chiedere dove necessario prova colore prima della tintura. Non tutti i colori potranno essere riprodotti fedelmente.

Sono necessarie prove preventive di finissaggio e tessitura per verificare che i capi soddisfino i requisiti richiesti.

MEMPHIS

Nm. 25000
51% (LI) LINEN
49% (CO) COTTON

KNITTING

Flat Machine Gauge 14 1 Ply

VENERE

Nm. 2/29
100% (LI) LINEN

KNITTING

Flat Machine Gauge 12 1 Ply

FINISHING

To achieve maximum dimensional stability and good softness, mill lightly in water with 2 grams of softener per litre, spin dry and tumble dry without overdrying. Steam press well.

NOTE

Due to the fact that linen is a natural fibre, it may cause slight colour difference among the lots supplied. In addition, due to linen natural "stiffness", spirality may appear on plain jersey when washed in water.

Colour reproduction can vary if we dye the same colour on yarns with different composition. We therefore ask you please to pay attention to the yarn used to make the card – Memphis, apart from colour 290149 and colour 026865 which have been dyed in Venere – and to ask for lab-dip approval before dyeing. It may be difficult to exactly reproduce all shades required.

Preliminary testing on knitting and finishing is necessary to be sure that garments meet your requirements.



INDEX

●▲ 001205 4B	027922 2A	▲ 290149 3D	290782 5A	290814 6C
026865 4C	●▲ 099054 4A	290762 1A	●▲ 290785 6D	290815 2D
027563 5C	●▲ 099070 6E	290767 5D	290810 2B	290816 3E
027565 1B	205832 4D	290768 1D	290811 6B	290817 5E
027911 1E	205836 4E	290773 3C	290812 1C	290820 3B
027917 3A	205915 5B	290779 2E	290813 2C	● 290821 6A

“●” : colori disponibili in MEMPHIS Nm. 25000 / available colours in MEMPHIS Nm. 25000

“▲” : colori disponibili in VENERE Nm. 2/29 / available colours in VENERE Nm. 2/29



ZEGNA BARUFFA LANE BORGOSIESIA S.p.A.

FILATURA IN VALLE MOSSO - ITALY

WWW.BARUFFA.COM

