


RIBES Nm. 16000 - 62% (LI) 38% (WV)

1

2

3


A



541653




541656 ●



541659 ●

B



541662



541663



541660

C



541654 ●




541657



541666


D



541655 ●



541664




541661

E




541658



541667

F



541665

## RIBES

Nm. 16000

62% (LI) LINO

38% (WV) LANA EXTRAFINE

## IMPIEGO

Rett. Fin. 14

a 1 capo

## FINISSAGGIO

Un normale vaporizzo durante lo stiro è sufficiente per ottenere una buona mano.

Per raggiungere la massima stabilità dimensionale e una buona morbidezza consigliamo di procedere con una leggera follatura in acqua con ammorbidente, centrifugare ed asciugare in tumbler a 85° circa senza essiccare. Stirare con abbondante vapore.

## NOTA

Segnaliamo che il lino, fibra naturale, non sempre presenta uniformità di colore sul greggio, perciò non possiamo escludere differenze di tonalità fra le forniture.

Una superficie leggermente irregolare è caratteristica propria del lino e sua positiva peculiarità. Inoltre a causa della sua naturale "rigidità" il lino può evidenziare spirality nella maglia rasata dopo il lavaggio in acqua.

Sono necessarie prove preventive di tessitura e finissaggio per verificare che i capi soddisfino i requisiti richiesti.

## RIBES

Nm. 16000

62% (LI) LINEN

38% (WS) EXTRAFINE WOOL

## KNITTING

Flat Machine Gauge 14

1 Ply

## FINISHING

Normal steam pressing is sufficient to give garments a good handle.

To achieve maximum dimensional stability and a good softness, our suggestion is to lightly finish in water with softener, spin dry and tumble dry at approximately 85°, without exceeding in drying. Steam pressing is enough to give garments a good handfeel.

## NOTE

Due to the fact that linen is a natural fibre, the colour of raw white yarn can vary from lot to lot and may therefore cause slight colour difference among the lots supplied.

A delicately uneven surface is one of linen's exquisite peculiarities. In addition, due to linen natural "stiffness", spirality may appear on plain jersey when washed in water.

**Preliminary testing on knitting and finishing is necessary to be sure that garments meet your requirements.**



## INDEX

541653	1A	541658	2E	541663	2B
● 541654	1C	● 541659	3A	541664	2D
● 541655	1D	541660	3B	541665	2F
● 541656	2A	541661	3D	541666	3C
541657	2C	541662	1B	541667	3E

“●” : colori disponibili in RIBES Nm. 16000 / available colours in RIBES Nm. 16000



ZEGNA BARUFFA LANE BORGOSIESA S.p.A.

FILATURA IN VALLE MOSSO - ITALY



FOLLOW US ON  
Facebook - The Italian Yarn  
www.facebook.com/BaruffaTheItalianYarn