

SIRIO SILVER - SIRIO GOLD

Nm. 32000

84% (WV) LANA SUPER

9% (PA) POLIAMMIDE

7% (PL) POLIESTERE METALLIZZATO LUREX

IMPIEGO

Rett. Fin. 16 - 18 F.F. Cotton 27 - 30 GG a 1 capo

SELENE

Nm. 27000

72% (WV) LANA SUPER

15% (PA) POLIAMMIDE

13% (PL) POLIESTERE METALLIZZATO LUREX

IMPIEGO

Rett. Fin. 16 - 18 F.F. Cotton 27 - 30 GG a 1 capo

MIRA

Nm. 9000

72% (WV) LANA SUPER

15% (PA) POLIAMMIDE

13% (PL) POLIESTERE METALLIZZATO LUREX

IMPIEGO

Rett. Fin. 7 a 1 capo

FINISSAGGIO

Con un semplice stiro e abbondante vaporizzo si ottiene una maglia di ottimo aspetto.

Per raggiungere buona stabilità dimensionale e mano più morbida consigliamo una leggera follatura dei teli o dei capi in acqua tiepida con 2 gr./lt. di ammorbidente, quindi di centrifugare ed asciugare in tumbler senza eccedere nell'essiccazione. Finire stirando con abbondante vapore.

Sono necessarie prove preventive di finissaggio e tessitura per verificare che i capi soddisfino i requisiti richiesti.

SIRIO SILVER - SIRIO GOLD

Nm. 32000

84% (WV) SUPER WOOL

9% (PA) POLYAMIDE

7% (PL) POLYESTER METALIZED LUREX

KNITTING

Rett. Fin. 16 - 18 F.F. Cotton 27 - 30 GG a 1 capo

SELENE

Nm. 27000

72% (WV) SUPER WOOL

15% (PA) POLYAMIDE

13% (PL) POLYESTER METALIZED LUREX

KNITTING

Rett. Fin. 16 - 18 F.F. Cotton 27 - 30 GG a 1 capo

MIRA

Nm. 9000

72% (WV) SUPER WOOL

15% (PA) POLYAMIDE

13% (PL) POLYESTER METALIZED LUREX

KNITTING

Rett. Fin. 7 a 1 capo

FINISHING

Pressing with a lot of steam will give an excellent and even appearance.

To achieve maximum dimensional stability and good softness we suggest to lightly mill in water with 2 grams of softener per litre, spin dry and tumble dry without overdrying.

Steam press well.

Preliminary testing on knitting and finishing is necessary to be sure that garments meet your requirements.




INDEX

027867 s	4A	027922 g	1A	* 027977 s	5A
027898 s	5C	027933 g	1B	028014 s	6C
● 027899 s	6A	027934 g	1C	028017 g	3A
027902 g	3C	● 027937 s	5B	● 205832 g	4C
027907 s	2A	027947 g	3B	● 205832 s	2C
● 027908 s	2B	* 027974 s	4B	205839 s	6B


“●” : colori disponibili in SIRIO SILVER o GOLD / available colours in SIRIO SILVER or GOLD

“*” : colori disponibili in SELENE o MIRA / available colours in SELENE or MIRA


1 2 3 4 5 6



027922 g




027907 s




028017 g




027867 s




027977 s*




027899 s ●




027933 g




027908 s ●




027947 g



027974 s* B O, SA




027937 s ●




205839 s




027934 g




205832 s ●




027902 g




205832 g ●




027898 s




028014 s




SIRIO SILVER



SIRIO GOLD



SELENE*



MIRA*

E' importante notare che, a parità di codice, l'effetto ottico del colore cambia notevolmente a seconda dell'articolo sul quale viene tinto, anche a causa del riflesso caldo o freddo del metallo (vedi campioni su questa pagina). Consigliamo di chiedere una prova di laboratorio per colori non presenti in cartella.

We wish to point out that the visual perception of a colour - the colour code being equal - very much varies depending on the type of yarn on which it is dyed, due to the warm or cool metal reflection (look at the samples on this page). It is advisable to ask for a lab-dip if you wish to order a colour which is not included in this colours card.