

SIRIO SILVER - SIRIO GOLD Nm. 32000 - 84% (WV) 9% (PA) 7% (PL)


SELENE Nm. 27000 - 72% (WV) 15% (PA) 13% (PL)

1


2

3


A



027867 s




202128 s



027907 s


B



027974 s




027906 s




203785 s

C



027977 s




027243 s




027956 s


D



028037 s




027896 s




207343 s ●

E



205832 s ●



205832 g ●




205834 s


F



027908 s ●




028056 g ●



205892 s

SELENE, colori disponibili per la campionatura



027974



027977



205832

SIRIO SILVER - SIRIO GOLD

Nm. 32000

84% (WV) LANA SUPER

9% (PA) POLIAMMIDE

7% (PL) POLIESTERE METALLIZZATO LUREX

IMPIEGO

Rett. Fin. 16 - 18 F.F. Cotton 27 - 30 GG a 1 capo

SELENE

Nm. 27000

72% (WV) LANA SUPER

15% (PA) POLIAMMIDE

13% (PL) POLIESTERE METALLIZZATO LUREX

IMPIEGO

Rett. Fin. 16 - 18 F.F. Cotton 27 - 30 GG a 1 capo

FINISSAGGIO

Con un semplice stiro e abbondante vaporizzo si ottiene una maglia di ottimo aspetto.

Per raggiungere buona stabilità dimensionale e mano più morbida consigliamo una leggera follatura dei teli o dei capi in acqua tiepida con 2 gr./lt. di ammorbidente, quindi di centrifugare ed asciugare in tumbler senza eccedere nell'essiccazione. Finire stirando con abbondante vapore.

Sono necessarie prove preventive di finissaggio e tessitura per verificare che i capi soddisfino i requisiti richiesti.

SIRIO SILVER - SIRIO GOLD

Nm. 32000

84% (WV) SUPER WOOL

9% (PA) POLYAMIDE

7% (PL) POLYESTER METALIZED LUREX

KNITTING

Flat Machine 16 - 18 F.F. Cotton 27 - 30 GG 1 ply

SELENE

Nm. 27000

72% (WV) SUPER WOOL

15% (PA) POLYAMIDE

13% (PL) POLYESTER METALIZED LUREX

KNITTING

Flat Machine 16 - 18 F.F. Cotton 27 - 30 GG 1 ply

FINISHING

Pressing with a lot of steam will give an excellent and even appearance.

To achieve maximum dimensional stability and good softness we suggest to lightly mill in water with 2 grams of softner per litre, spin dry and tumble dry without overdrying.

Steam press well.

Preliminary testing on knitting and finishing is necessary to be sure that garments meet your requirements.



INDEX

027243 s	2C	027956 s	3C	203785 s	3B
027867 s	1A	027974 s	1B	● 205832 s	1E
027896 s	2D	027977 s	1C	● 205832 g	2E
027906 s	2B	028037 s	1D	205834 s	3E
027907 s	3A	● 028056 g	2F	205892 s	3F
● 027908 s	1F	202128 s	2A	● 207343 s	3D

“●” : colori disponibili in SIRIO SILVER o GOLD / available colours in SIRIO SILVER or GOLD

“*” : colori disponibili in SELENE / available colours in SELENE



ZEGNA BARUFFA LANE BORGOSIESIA S.p.A.

FILATURA IN VALLE MOSSO - ITALY

WWW.BARUFFA.COM

