



CLIMATIK

Z65761

Nm 2/48 Tex 20,8x2

COMPOSIZIONE 70% (WV) lana extrafine 30% (CLY) lyocell	COMPOSITION 70% (WV) extrafine wool 30% (CLY) lyocell
COLORI Si possono tingere colori a richiesta. <i>I colori da noi forniti hanno valori di solidità secondo quanto previsto da Woolmark. Questi valori non garantiscono l'utilizzo in rigato, specialmente per i forti contrasti. Eventuali esigenze particolari dovranno essere specificate all'atto dell'ordine.</i> Non tutti i toni possono essere riprodotti fedelmente: Considerando la particolare composizione dell'esclusiva fibra CLIMA certi colori, come puro bianco o sbiancati, possono riuscire meno brillanti. Per questi toni è consigliato un preventivo studio colore.	COLOURS Customer's colour can be dyed upon request. <i>We guarantee that for every colour we dye, the colour fastness values are as per woolmark standard. Some colours might not be suitable for knitting stripes or other knitted pattern if using very contrasting colours. Any other special fastness should be expressly requested.</i> It may be difficult to exactly reproduce all the shades required: Taking in consideration the special characteristic of the exclusive CLIMA fibre, pure white and bleached colours can result less bright than normal. We advise, in these cases, to do preliminary lab dips.
QUANTITA' OTTIMALI Colori a richiesta: kg.60-100-150-300. E' possibile produrre quantità di kg. 24-30-40 con i supplementi previsti dalle nostre condizioni generali di vendita.	IDEAL QUANTITIES Custom-made colours: kg.60-100-150-300. 24-30-40 kg lots are available on request at extra charge according to our General Sales Conditions.
CARATTERISTICHE Filato speciale con caratteristiche di termoregolazione.	FEATURES Special Yarn with thermoregulation characteristic.
IMPIEGO Rett. Fin. 14 FF Cotton 27-30 gg 1 capo Rett. Fin. 12 FF Cotton 21 gg 2 capi	USE Flat machine 14 FF Cotton 27-30 gg 1 ply Flat machine 12 FF Cotton 21 gg 2 plies
FINISSAGGIO Con un semplice stiro con abbondante vaporizzo si ottiene un ottimo aspetto della maglia. Per esaltare al meglio la sofficità e la gonfiezza del filato si consiglia una leggera follatura in acqua per 3-5 minuti con ammorbidente al 2-3% sul peso merce, ad una temperatura non superiore a 35°C. Centrifugare. Asciugare in tumbler avendo cura di non essiccare troppo. Finire stirando con abbondante vapore.	FINISHING A normal pressing with a lot of steam will give an excellent regular aspect. To enhance softness and bulkiness of the yarn, we suggest a light milling for 3-5 minutes in water using a wool-softener in ratio of 2-3% of the garments' weight, at a temperature of less than 35°C. Centrifuge. Tumble-dry without over-drying. Steam-press thoroughly.
ETICHETTATURA	LABELLING



STAGIONE AUTUNNO - INVERNO 2011 - 2012

Data Rilascio: 22/06/10

Documento Approvato