

MISTRAL NM. 2/48

53% (WV) LANA EXTRAFINE
47% (CO) COTONE

IMPIEGO

RETT. FIN. 14
F.F. COTTON 21 - 24 GG

1 CAPO
1 CAPO

SILVER NM. 2/50

48% (WV) LANA EXTRAFINE
47% (CO) COTONE
5% (WS) CASHMERE

IMPIEGO

RETT. FIN. 14
F.F. COTTON 21 - 24 GG

1 CAPO
1 CAPO

FINISSAGGIO

CON UN SEMPLICE STIRO CON ABBONDANTE VAPORIZZO SI OTTIENE UN OTTIMO ASPETTO DELLA MAGLIA. PER ESALTARE AL MEGLIO LA SOFFICITÀ E LA GONFIEZZA DEL FILATO SI CONSIGLIA UNA LEGGERA FOLLATURA IN ACQUA PER 3-5 MINUTI CON AMMORBIDENTE AL 2-3% SUL PESO MERCE, AD UNA TEMPERATURA NON SUPERIORE A 35°C. CENTRIFUGARE. ASCIUGARE IN TUMBLER AVENDO CURA DI NON ESSICARE TROPPO. FINIRE STIRANDO CON ABBONDANTE VAPORE.

MISTRAL NM. 2/48

53% (WV) EXTRAFINE WOOL
47% (CO) COTTON

KNITTING

FLAT MACHINE 14
F.F. COTTON 21 - 24 GG

1 PLY
1 PLY

SILVER NM. 2/50

48% (WV) EXTRAFINE WOOL
47% (CO) COTONE
5% (WS) CASHMERE

KNITTING

FLAT MACHINE 14
F.F. COTTON 21 - 24 GG

1 PLY
1 PLY

FINISHING

A NORMAL PRESSING WITH A LOT OF STEAM WILL GIVE AN EXCELLENT REGULAR ASPECT. TO ENHANCE SOFTNESS AND BULKINESS OF THE YARN, WE SUGGEST A LIGHT MILLING FOR 3-5 MINUTES IN WATER USING A WOOL-SOFTENER IN RATIO OF 2-3% OF THE GARMENT'S WEIGHT, AT A TEMPERATURE OF LESS THAN 35°C. CENTRIFUGE. TUMBLE-DRY WITHOUT OVER-DRYING. STEAM PRESS THOROUGHLY GIVING MUCH STEAM.



INDEX

● 008800 8/E	510417 6/B	● 541470 8/C
017007 2/B	540993 5/A	541471 3/E
017008 1/A	541011 8/D	541473 1/C
017009 9/A	541111 5/B	541474 1/D
017010 9/B	541163 3/B	541475 1/E
017014 7/B	541383 3/A	541476 2/C
017015 4/A	541436 3/C	541477 2/D
017016 4/B	541437 1/B	541478 2/E
017019 8/B	541463 7/D	541479 6/D
017021 7/A	541464 3/D	541481 7/C
● 099054 2/A	541465 4/C	541482 7/E
● 099070 9/E	541466 4/D	541483 9/C
255082 8/A	541467 4/E	661825 6/E
255088 5/D	541468 5/E	669734 6/A
255098 6/C	● 541469 5/C	669739 9/D

“●”: COLORI DISPONIBILI IN SILVER

“●”: COLOURS AVAILABLE IN SILVER

MISTRAL NM. 2/48 - 53% (WV) - 47% (CO) - SILVER NM. 2/50 - 48% (WV) - 47% (CO) - 5% (WS)

1

2

3

A

017008

099054

541383

B

541437

017007

541163

C

541473

541476

541436

D

541474

541477

541464

E

541475

541478

541471



4

A

017015

B

017016

C

541465

D

541466

E

541467



5

540993

541111

541469

255088

541468



6

669734

510417

255098

541479

661825



7

8

9

A

017021

255082

017009

B

017014

017019

017010

C

541481

541470

541483

D

541463

541011

669739

E

541482

008800

099070